

May 1994

Magnetization reversal in compositionally modulated Tb/Fe multilayers (abstract)

Roger D. Kirby

University of Nebraska-Lincoln, rkirby1@unl.edu

J. X. Shen

University of Nebraska - Lincoln

David J. Sellmyer

University of Nebraska-Lincoln, dsellmyer@unl.edu

Follow this and additional works at: http://digitalcommons.unl.edu/physics_kirby



Part of the [Physics Commons](#)

Kirby, Roger D.; Shen, J. X.; and Sellmyer, David J., "Magnetization reversal in compositionally modulated Tb/Fe multilayers (abstract)" (1994). *Roger Kirby Publications*. 16.

http://digitalcommons.unl.edu/physics_kirby/16

This Article is brought to you for free and open access by the Research Papers in Physics and Astronomy at DigitalCommons@University of Nebraska - Lincoln. It has been accepted for inclusion in Roger Kirby Publications by an authorized administrator of DigitalCommons@University of Nebraska - Lincoln.

Magnetization reversal in compositionally modulated Tb/Fe multilayers (abstract)

Roger D. Kirby, J. X. Shen, and D. J. Sellmyer

*Behlen Laboratory of Physics and Center for Materials Research and Analysis, University of Nebraska,
Lincoln, Nebraska 68588-0111*

We have prepared compositionally modulated Tb($X \text{ \AA}$)/Fe(5 \AA) thin film multilayers with X ranging from 3.5 to 7 \AA by magnetron sputtering on glass substrates. Magnetization measurements using SQUID and alternating gradient force magnetometers show that these samples have uniaxial anisotropies (K_u) up to 10^7 erg/cm^3 and saturation magnetizations (M_s) between 50 and 350 emu/cm^3 . Constant field magnetization reversal measurements at room temperature show that these samples reverse by slow nucleation followed by relatively rapid domain wall motion. The samples with larger uniaxial anisotropies and smaller saturation magnetizations reverse completely for applied fields less than the coercivity, while those samples on the other end of the spectrum do not. The magnetization reversal curves are correlated with the shapes of the hysteresis loops, and the experimental results are interpreted using a recently developed uniaxial anisotropy model of magnetization reversal.¹

Research sponsored by the NSF under Grant No. DMR-8918889 and by the Research Corporation.

¹R. D. Kirby, J. X. Shen, R. J. Hardy, and D. J. Sellmyer, Phys. Rev. B (to be published).