University of Nebraska - Lincoln Digital Commons@University of Nebraska - Lincoln

Roger Kirby Publications

Research Papers in Physics and Astronomy

5-14-1994

Magnetization reversal in compositionally modulated Tb/Fe multilayers (abstract)

Roger D. Kirby University of Nebraska-Lincoln, rkirby1@unl.edu

J. X. Shen University of Nebraska - Lincoln

David J. Sellmyer University of Nebraska-Lincoln, dsellmyer@unl.edu

Follow this and additional works at: http://digitalcommons.unl.edu/physics kirby



Part of the Physics Commons

Kirby, Roger D.; Shen, J. X.; and Sellmyer, David J., "Magnetization reversal in compositionally modulated Tb/Fe multilayers (abstract)" (1994). Roger Kirby Publications. Paper 16. http://digitalcommons.unl.edu/physics_kirby/16

This Article is brought to you for free and open access by the Research Papers in Physics and Astronomy at Digital Commons@University of Nebraska -Lincoln. It has been accepted for inclusion in Roger Kirby Publications by an authorized administrator of Digital Commons@University of Nebraska -Lincoln.

Magnetization reversal in compositionally modulated Tb/Fe multilayers (abstract)

Roger D. Kirby, J. X. Shen, and D. J. Sellmyer
Behlen Laboratory of Physics and Center for Materials Research and Analysis, University of Nebraska,
Lincoln, Nebraska 68588-0111

We have prepared compositionally modulated Tb(X Å)/Fe(5 Å) thin film multilayers with X ranging from 3.5 to 7 Å by magnetron sputtering on glass substrates. Magnetization measurements using SQUID and alternating gradient force magnetometers show that these samples have uniaxial anisotropies (K_u) up to 10^7 erg/cm³ and saturation magnetizations (M_s) between 50 and 350 emu/cm³. Constant field magnetization reversal measurements at room temperature show that these samples reverse by slow nucleation followed by relatively rapid domain wall motion. The samples with larger uniaxial anisotropies and smaller saturation magnetizations reverse completely for applied fields less than the coercivity, while those samples on the other end of the spectrum do not. The magnetization reversal curves are correlated with the shapes of the hysteresis loops, and the experimental results are interpreted using a recently developed uniaxial anisotropy model of magnetization reversal.

Research sponsored by the NSF under Grant No. DMR-8918889 and by the Research Corporation.

¹R. D. Kirby, J. X. Shen, R. J. Hardy, and D. J. Sellmyer, Phys. Rev. B (to be published).