

1-1-1992

Kinetic Analysis of Competing Intramolecular and Intermolecular Polymerization Reactions

Hossein Nouredдини

Department of Chemical Engineering, University of Nebraska-Lincoln, hnouredd@unlnotes.unl.edu

Delmar C. Timm

University of Nebraska-Lincoln, dtimm1@unl.edu

Follow this and additional works at: <http://digitalcommons.unl.edu/chemengmolecular>



Part of the [Chemical Engineering Commons](#)

Nouredдини, Hossein and Timm, Delmar C., "Kinetic Analysis of Competing Intramolecular and Intermolecular Polymerization Reactions" (1992). *Papers in Molecular Chemistry*. 5.

<http://digitalcommons.unl.edu/chemengmolecular/5>

This Article is brought to you for free and open access by the Chemical and Biomolecular Engineering Research and Publications at DigitalCommons@University of Nebraska - Lincoln. It has been accepted for inclusion in Papers in Molecular Chemistry by an authorized administrator of DigitalCommons@University of Nebraska - Lincoln.

H. Nouredini and D. C. Timm, *Kinetic Analysis of Competing Intramolecular and Intermolecular Polymerization Reactions*, *Macromolecules*; 1992; 25(6); 1725-1730.

Kinetic Analysis of Competing Intramolecular and Intermolecular Polymerization Reactions

H. Nouredini and D. C. Timm

Department of Chemical Engineering, University of Nebraska, Lincoln, Nebraska

Received August 21, 1990; Revised Manuscript Received December 8, 1991

Macromolecules; 1992; 25(6); 1725-1730.

Copyright © 1992 American Chemical Society.

The American Chemical Society allows the posting of only the title, abstract, tables, and figures from articles appearing in the *Macromolecules*.


This article is available at published online at:

<http://pubs.acs.org/cgi-bin/archive.cgi/mamobx/1992/25/i06/pdf/ma00032a016.pdf>

ABSTRACT: Kinetic reaction theory was used to model a step-growth, the most polymerization of a monomer of f functional groups. Intermolecular additions were represented by second-order and intramolecular reactions were expressed by first-order rate expressions. All functional groups were assumed to react with equal reactivity. Independent variables are degree of polymerization i , extent of cross-linking j , and conversion ρ . The normalized rate constant for intramolecular reactions is c . The solution for the normalized population density distribution is

$$P_{ij} = \frac{f(f-1)!(f-2)!/2!}{2^{j-1}[(f-2)j-j+1]!(f-2)!/2-j-1, 2, j!} \frac{c^j \rho^{f-j} [(1-\rho + c)(1-\rho)]^{(f-2)j-2j+1}}{(1+c)^{f-2j}}$$

subject to $0 \leq i \leq (f-2)j/2 - 1$ and $c \geq 0$. Formulas for the number-, mass-, and cross-link-average molecular weights were derived.






Figure 2. Calculated vs actual degree of cure for a 2 K/min scan by DSC analysis.