

University of Nebraska - Lincoln

DigitalCommons@University of Nebraska - Lincoln

Robert G. Fuller Publications and Presentations

Research Papers in Physics and Astronomy

July 1967

ANION CONTRIBUTIONS TO THE ELECTRICAL CONDUCTIVITY OF ALKALI CHLORIDES

Robert Fuller
rfuller@neb.rr.com

M.H. Reilly
Naval Research Laboratory, Washington, D. C.

Follow this and additional works at: <https://digitalcommons.unl.edu/physicsfuller>



Part of the [Physics Commons](#)

Fuller, Robert and Reilly, M.H., "ANION CONTRIBUTIONS TO THE ELECTRICAL CONDUCTIVITY OF ALKALI CHLORIDES" (1967). *Robert G. Fuller Publications and Presentations*. 19.

<https://digitalcommons.unl.edu/physicsfuller/19>

This Article is brought to you for free and open access by the Research Papers in Physics and Astronomy at DigitalCommons@University of Nebraska - Lincoln. It has been accepted for inclusion in Robert G. Fuller Publications and Presentations by an authorized administrator of DigitalCommons@University of Nebraska - Lincoln.

(30-1)-2391 and NYO-2391-49. Additional support was received from the Advanced Research Projects Agency through the use of space and technical facilities of the Materials Science Center at Cornell University.

¹A. J. Sievers, Phys. Rev. Letters 13, 310 (1964); R. Weber, Phys. Letters 12, 311 (1964); A. J. Sievers and S. Takeno, Phys. Rev. 140, 1030 (1965); A. J. Sievers, R. W. Alexander, Jr., and S. Takeno, Solid State Commun. 4, 483 (1966).

²P. G. Dawber and R. J. Elliott, Proc. Roy. Soc. (London) 273, 222 (1963); G. Benedek and G. F. Nardelli, Phys. Rev. 155, 1004 (1967); A. A. Maradudin, in Solid State Physics, edited by F. Seitz and D. Turnbull (Academic Press, Inc., New York, 1966), Vols. 18 and 19.

³I. G. Nolt and A. J. Sievers, Phys. Rev. Letters 16, 1103 (1966).

⁴I. G. Nolt and A. J. Sievers, Bull. Am. Phys. Soc. 12, 79 (1967), and to be published.

⁵G. Lombardo and R. O. Pohl, Phys. Rev. Letters 15, 291 (1965); H. S. Sack and M. S. Moriarty, Solid State Commun. 3, 936 (1965); A. Lakatos and H. S. Sack, Solid State Commun. 4, 315 (1966); N. E. Byer and H. S. Sack, Phys. Rev. Letters 17, 72 (1966).

⁶E. Kraetzig, T. Timusk, and W. Martienssen, Phys.

Status Solidi 10, 709 (1965); W. Dreybrodt and K. Füssgaenger, *ibid.*, 18, 133 (1966).

⁷A. Smakula, N. C. Maynard, and A. Repucci, Phys. Rev. 130, 113 (1963).

⁸W. Barth and B. Fritz, Phys. Status Solidi 19, 515 (1967).

⁹For the KBr host lattice containing about 0.02 mole% LiBr, the KCl constituent ranged from 0 to 14.2% and the KI constituent ranged from 0 to 4.5 mole%. For the KCl host lattice containing about 0.02 mole% LiCl, the KBr constituent ranged from 0 to 9.2 mole%.

¹⁰L. Vegard, Z. Physik 5, 17 (1921).

¹¹S. P. Bowen, M. Gomez, J. A. Krumhansl, and J. A. D. Matthew, Phys. Rev. Letters 16 1105 (1966); and also, M. Gomez, S. P. Bowen, and J. A. Krumhansl, Phys. Rev. 153, 1009 (1967).

¹²Recent studies by H. K. A. Kan show that it is not possible to obtain homogeneous solid solutions for KBr containing more than 10 mole% KI with the normal Kyropoulos growing method. H. K. A. Kan, thesis, Cornell University, 1966, Materials Science Center Report No. 427 (unpublished).

¹³W. Cochran, Advan. Phys. 9, 387 (1960); 10, 401 (1961).

¹⁴H. S. Sack, private communication.

ANION CONTRIBUTIONS TO THE ELECTRICAL CONDUCTIVITY OF ALKALI CHLORIDES

R. G. Fuller and M. H. Reilly*

Naval Research Laboratory, Washington, D. C.

(Received 8 May 1967)

The measured electrical conductivity of pure RbCl is separated into the usual anion and cation contributions with activation energies of 2.55 and 1.58 eV, respectively. By comparison with corresponding results for KCl and NaCl it is found that the alkali-chloride anion and cation activation energies differ most for nearly equal anion and cation radii. We conclude from this anomalous trend that an extension of conventional theory is required.

The intrinsic electrical conductivity of alkali-halide crystals is, in principle, the sum of the anion (-) and cation (+) contributions and is expressible as the sum of two exponentials in the following way:

$$\begin{aligned} \sigma T &= \sigma_a T + \sigma_c T \\ &= A_0 \exp(-W_a/kT) + C_0 \exp(-W_c/kT), \quad (1) \end{aligned}$$

where σ is the conductivity ($\Omega^{-1} \text{ cm}^{-1}$); σ_a and σ_c are the anion and cation contributions to σ , respectively; T is the absolute temperature ($^{\circ}\text{K}$); W_a and W_c are the anion and cation activation energies for conduction, respectively; and A_0 and C_0 are constants. In general, W_a is not equal to W_c . Therefore, $\ln\sigma T$ is not a linear function of $1/T$. Experimental data

from many experiments¹⁻⁶ have indicated, however, that σT could be expressed as a single $\exp(-W/kT)$ term. These same experiments gave evidence that the electric current was carried by mobile cations, and quite naturally the idea developed that anions were relatively immobile. Allnatt and Jacobs⁷ observed curvature in a plot of $\ln\sigma T$ vs $1/T$ for pure KCl, which they associated with additional anion conductivity. This was substantiated by subsequent chlorine-ion diffusion measurements on KCl.⁸

The intrinsic electrical conductivity of RbCl crystals has been measured in the temperature range 550 to 700 $^{\circ}\text{C}$ to look for evidence of anion contributions to the conductivity. Figure 1 shows the results, plotted in the usual way. The measurements were made using standard ac bridge techniques at 1 kHz. The tempera-




FIG. 1. Temperature dependence of the electrical conductivity of "pure" RbCl. The least-squares fit of the experimental data and 1.23 times $\sigma_c T$ [see Eq. (1) of text] inferred from G. Arai and J. G. Mullen [Phys. Rev. **143**, 663 (1966)] are shown as solid and dashed lines, respectively.

ture uncertainty was 0.2°C and the experimental error in the magnitude of the conductivity was $\pm 2\%$ (represented by the circles in Fig. 1).

The analysis of the RbCl data was done using Eq. (1) and the method of least squares. The solid curve in Fig. 1 is the sum of the anion and cation contributions to the conductivity as determined by this analysis. The numerical results from our analysis of the RbCl data are shown in Table I along with values reported for NaCl by Laurance⁹ and Dreyfus and Nowick,⁶ and for KCl by Beaumont and Jacobs.¹⁰ The estimated computational uncertainties for RbCl are a factor of 2 for A_0 and C_0 and ± 0.05 eV

for W_a and W_c . The analysis of the RbCl data was modified to include the existence of long-range Coulomb interactions between the cation and anion vacancies. This modification was made using the Debye-Hückel theory for electrolytic solutions,¹¹ and the results are given in parentheses in Tables I and II. Our identification of anion and cation components of the RbCl conductivity is based on the 1.99-eV activation energy of Rb-ion diffusion in RbCl.¹² This value sets an upper limit on W_c , since it was not corrected for the vacancy-pair contribution to the diffusion. It therefore appears consistent with our value of 1.58 eV.

The electrical conductivity data of Fig. 1 can be compared with diffusion coefficient (D_{Rb}) for Rb^+ in RbCl.¹² If the vacancy pair contribution is neglected, the Einstein relation gives the cation contribution to the conductivity $\sigma_c T = 3.23 \times 10^7 D_{\text{Rb}}$.¹³ This expression, multiplied by the constant 1.23 for closer comparison with the measured values of σT , is represented by the dashed line in Fig. 1. Thus, as for NaCl and KCl, the intrinsic electrical conductivity cannot be explained as only cation conductivity. The curvature of the plot of $\ln \sigma T$ vs $1/T$ for RbCl is greater than the similar curvature reported for KCl.¹⁰ It follows that for RbCl the values for the difference in activation energies, $W_a - W_c$, and the ratio of the pre-exponential constants, A_0/C_0 , must be even larger than the KCl values¹⁰ of 0.33 eV and 80.

Values for the anion transport number, the fraction of current carried by the anion, were calculated from Table I and are shown in Table II. These values agree with the two values obtained by the direct measurements of Haven.¹⁴ Apparently, the reported linearity⁶ of a plot of $\ln \sigma T$ vs $1/T$ for NaCl occurred not because of low anion mobility but because a precise measurement of the conductivity of NaCl had not been

Table I. Contributions to ionic conductivity.

	($^\circ\text{K}/\Omega \text{ cm}$)		
	Anion (-) $A_0 \exp(-W_a/kT)$	Cation (+) $C_0 \exp(-W_c/kT)$	A_0/C_0
NaCl	$1.2 \times 10^9 \exp(-2.07 \text{ eV}/kT)^a$	$4.7 \times 10^8 \exp(-1.86 \text{ eV}/kT)^b$	2
KCl	$3.85 \times 10^9 \exp(-2.17 \text{ eV}/kT)^c$	$4.63 \times 10^7 \exp(-1.84 \text{ eV}/kT)^c$	80
RbCl	$8.85 \times 10^{11} \exp(-2.55 \text{ eV}/kT)$ $[2.55 \times 10^{11} \exp(-2.47 \text{ eV}/kT)]$	$3.58 \times 10^6 \exp(-1.58 \text{ eV}/kT)$ $[1.79 \times 10^6 \exp(-1.53 \text{ eV}/kT)]$	25×10^4 $[14 \times 10^4]$

^aRef. 9.

^bRef. 6.

^cRef. 19.

Table II. Anion transport numbers.

Temp. (°C)	$\sigma_{\text{anion}}/\sigma_{\text{total}}$			
	NaCl	KCl	RbCl	RbCl ^b
747	0.20	0.65	...	
707	0.18 (0.14 ^a)	0.62	0.70 (0.68)	0.33
620	0.15	0.52 (0.54 ^a)	0.43 (0.41)	0.19
546	0.12	0.43	0.19 (0.19)	0.28

^aTransport numbers measured by Y. Haven, Proc. Brit. Ceram. Soc. 1, 93 (1964).

^bTransport numbers computed using our conductivity data and Rb⁺ diffusion in RbCl (Ref. 12) uncorrected for vacancy pairs.

made for the entire intrinsic region (550 to 790°C) in KCl and RbCl the anions make contributions to the conductivity at 707°C which are even larger than that of NaCl but which decrease significantly with decreasing temperature.

For the alkali chlorides, as the difference between anion and cation radii decreases from 0.42 Å in NaCl to 0.01 Å in RbCl,¹⁵ the difference between anion and cation activation energies increases from 0.2 to 1.0 eV. This trend is opposite to that shown in the calculations of Guccione, Tosi, and Asdenti.¹⁶

The ratio of pre-exponential terms can be expressed as

$$\frac{A_0}{C_0} = \frac{\nu_a}{\nu_c} \exp[(\Delta s_a - \Delta s_c)/k], \quad (2)$$

where ν is a vibration frequency and Δs is an activation entropy. Typical values for ν and Δs in these crystals are $5 \times 10^{12}/\text{sec}$ and $3k$, respectively.⁶ Assuming $\nu_a = \nu_c$, the A_0/C_0 values (Table I) give rise to unusually large values for the difference between anion and cation activation entropies, i.e., $(\Delta s_a - \Delta s_c) = 4.4k$ for KCl and $12k$ for RbCl. These anomalous values for $(\Delta s_a - \Delta s_c)$ are a direct consequence of the curvature of $\ln \sigma T$ vs $1/T$ and the assumed temperature independence of W_a and W_c . Curvature could be explained and more physically acceptable values of A_0/C_0 obtained if the activation energies were assumed to be slightly temperature dependent. Temperature-dependent activation energies could possibly be related to the apparent discrepancy between the low-temperature¹⁷ and high-temperature⁸ values for the anion migration energy in KCl.

The authors are grateful to Dr. C. C. Klick

and Dr. M. N. Kabler for many profitable discussions.

*National Research Council-National Academy of Science Postdoctoral Research Associate.

¹For several alkali halides, see W. Lehfeldt, Z. Physik 85, 717 (1933).

²For KCl, see H. Kelting and H. Witt, Z. Physik 126, 697 (1949).

³For NaCl, see H. W. Etzel and R. J. Maurer, J. Chem. Phys. 18, 1003 (1950).

⁴For KCl, see F. Kerkhoff, Z. Physik 130, 449 (1951).

⁵For KCl, see J. Aschner, thesis, University of Illinois, Urbana, Illinois, 1954 (unpublished).

⁶For NaCl and KCl, see R. W. Dreyfus and A. S. Nowick, J. Appl. Phys. Suppl. 33, 473 (1962).

⁷A. R. Allnatt and P. W. M. Jacobs, Trans. Faraday Soc. 58, 116 (1962).

⁸R. G. Fuller, Phys. Rev. 142, 524 (1966).

⁹The anion contribution was the result of a new analysis of the data for the chlorine-ion diffusion in NaCl previously reported by N. Laurance [Phys. Rev. 120, 57 (1960)]. Using a calcium ion-cation vacancy association energy of 0.31 eV, the results of the analysis were

$$D_{\text{anion}} = (22 \pm 2) \exp\left(-\frac{(2.07 \pm 0.05) \text{ eV}}{kT}\right) \text{ cm}^2/\text{sec},$$

$$D_{\text{vacancy pairs}} = (990 \pm 90) \exp\left(-\frac{(2.50 \pm 0.02) \text{ eV}}{kT}\right) \text{ cm}^2/\text{sec}.$$

For NaCl,

$$\sigma_{\text{anion}}^T = 5.25 \times 10^{17} D_{\text{anion}}.$$

¹⁰J. H. Beaumont and P. W. M. Jacobs, J. Chem. Phys. 45, 1496 (1966).

¹¹See A. B. Lidiard, in *Handbuch der Physik*, edited by S. Flügge (Springer-Verlag, Berlin, 1957), Vol. 20, pp. 307 and 309. The calculations were done with

$$(\epsilon - 1)/(\epsilon + 2) = 0.544 \exp(1.65 \times 10^{-4} T)$$

and

$$x_1 = x_2 = 57.3 \exp(-1.12 \text{ eV}/kT).$$

¹²G. Arai and J. G. Mullen, Phys. Rev. 143, 663 (1966).

¹³An expression for the vacancy-pair contribution to the Rb⁺ diffusion in RbCl can be obtained for our results and those of Arai and Mullen (Ref. 12). It is found that the vacancy-pair contribution is given by the expression

$$D_p \sim 5 \times 10^3 \exp(-2.46 \text{ eV}/kT),$$

and is of the order of the measure D_{Rb} .

¹⁴Y. Haven, Proc. Brit. Ceram. Soc. 1, 93 (1964).

¹⁵M. P. Tosi and F. G. Fumi, J. Phys. Chem. Solids 25, 45 (1964).

¹⁶R. Guccione, M. P. Tosi, and M. Asdente, J. Phys. Chem. Solids 10, 162 (1959).

¹⁷F. Lüty, Bull. Am. Phys. Soc. 12, 550 (1967).