

University of Nebraska - Lincoln

DigitalCommons@University of Nebraska - Lincoln

Xiao Cheng Zeng Publications

Published Research - Department of Chemistry

2010

Isomer identification and resolution in small gold clusters

Wei Huang

Brown University

Rhitankar Pal

University of Nebraska-Lincoln

Lei-Ming Wang

Washington State University, Richland

Xiao Cheng Zeng

University of Nebraska-Lincoln, xzeng1@unl.edu

Lai-Sheng Wang

Brown University, Providence, Rhode Island

Follow this and additional works at: <https://digitalcommons.unl.edu/chemzeng>

 Part of the [Chemistry Commons](#)

Huang, Wei; Pal, Rhitankar; Wang, Lei-Ming; Zeng, Xiao Cheng; and Wang, Lai-Sheng, "Isomer identification and resolution in small gold clusters" (2010). *Xiao Cheng Zeng Publications*. 105.

<https://digitalcommons.unl.edu/chemzeng/105>

This Article is brought to you for free and open access by the Published Research - Department of Chemistry at DigitalCommons@University of Nebraska - Lincoln. It has been accepted for inclusion in Xiao Cheng Zeng Publications by an authorized administrator of DigitalCommons@University of Nebraska - Lincoln.

Isomer identification and resolution in small gold clusters

Wei Huang,¹ Rhitankar Pal,² Lei-Ming Wang,³ Xiao Cheng Zeng,^{2,a)} and Lai-Sheng Wang^{1,b)}

¹Department of Chemistry, Brown University, Providence, Rhode Island, 02912, USA

²Department of Chemistry and Center for Materials and Nanoscience, University of Nebraska-Lincoln, Lincoln, Nebraska 68588, USA

³Department of Physics, Washington State University, 2710 University Drive, Richland, Washington 99354, USA

(Received 7 December 2009; accepted 6 January 2010; published online 5 February 2010)

A variety of experimental techniques are used to resolve energetically close isomers of Au_7^- and Au_8^- by combining photoelectron spectroscopy and *ab initio* calculations. Two structurally distinct isomers are confirmed to exist in the cluster beam for both clusters. Populations of the different isomers in the cluster beam are tuned using Ar-tagging, O_2 -titration, and isoelectronic atom substitution by Cu and Ag. A new isomer structure is found for Au_7^- , which consists of a triangular Au_6 unit with a dangling Au atom. Isomer-specific photoelectron spectra of Au_8^- are obtained from O_2 -titration experiment. The global minimum and low-lying structures of Au_7^- , Au_8^- , and MAu_n^- ($n=6,7$; $M=\text{Ag,Cu}$) are obtained through basin-hopping global minimum searches. The results demonstrate that the combination of well-designed photoelectron spectroscopy experiments (including Ar-tagging, O_2 -titration, and isoelectronic substitution) and *ab initio* calculation is not only powerful for obtaining the electronic and atomic structures of size-selected clusters, but also valuable in resolving structurally and energetically close isomers of nanoclusters. © 2010 American Institute of Physics. [doi:10.1063/1.3299292]

I. INTRODUCTION

The properties of nanoparticles are known to depend on both their size and shape. The discovery of catalytic activities of supported gold nanoparticles¹ has stimulated intense interests in the structures and properties of gaseous gold clusters,^{2–7} which provide atomically defined models for understanding the mechanisms of the catalytic effects of gold nanoparticles.⁸ Different techniques have been used to probe the structures of gold nanoclusters, including photoelectron spectroscopy (PES),⁹ ion mobility,^{10,11} infrared multiphoton dissociation spectroscopy,^{12,13} and trapped ion electron diffraction.¹⁴ While all these techniques are quite powerful, in particular, when combined with *ab initio* calculations in obtaining structural information, the identification and resolution of structurally and energetically close isomers have remained a considerable challenge.

Because of the theoretical difficulties presented by gold clusters as a result of the strong relativistic and spin-orbit effects,^{15–17} definitive experimental data are essential in helping elucidate their structures and chemical reactivity. In particular, in cases of structurally and energetically close isomers, it is critical to be able to identify contributions from different isomers and to obtain *isomer-specific* chemical and spectroscopic information. A variety of structures have been resolved experimentally and proposed theoretically for a range of gold clusters. The structures of gold cluster anions (Au_n^-) in the size range from $n=3$ to 20 have been studied using a combination of experimental techniques and density

functional theory (DFT) calculations, ranging from the planar [two-dimensional (2D)] clusters for $n \leq 12$,^{10,18–24} the tetrahedral Au_{20}^- ,²⁵ and the cage clusters for $n=16–18$.^{14,26–30} Even for relatively small gold clusters, the structures and, particularly, the isomer issues in a few cases still remain questionable and controversial and need more definitive experimental and theoretical evidence to be resolved.^{5,13,22,27,31–33}

Recently, we have shown that there are at least four co-existing isomers in the Au_{10}^- cluster beam³¹ using Ar-tagging and O_2 -titration techniques^{34,35} in combination with PES, revealing the structural diversity and complexity of small gold clusters. We have also observed that planar Au_n^- clusters, as well as the pyramidal Au_{20}^- , have stronger charge-induced intermolecular interactions with Ar, and used this property to obtain isomer-specific PES spectra for Au_{12}^- (Ref. 22) and obtained distinct experimental evidence that the cage-to-pyramid crossover occurs at Au_{18}^- .²⁸ Although Ar-tagging and O_2 -titration combined with PES have been proven very useful in resolving isomers of nanoclusters, there are deficiencies under certain circumstances. Ar-tagging is especially useful when the isomers have very different structures, for example, the 2D versus three-dimensional (3D) structures in Au_{12}^- .²² If the isomers have similar structures and thus similar charge-induced intermolecular interactions with Ar, it would be difficult to obtain isomer-specific spectra using the Ar-tagging method. O_2 -titration cannot be used for those clusters unreactive with O_2 , such as odd-sized Au_n^- clusters or isomers with similar O_2 reactivity. Ion mobility is especially useful in resolving geometrical structures of nanoclusters according to different

^{a)}Electronic mail: xczen@phase2.unl.edu.

^{b)}Electronic mail: lai-sheng_wang@brown.edu.

collision cross sections of different isomers.^{10,11} However, just like Ar-tagging, when two isomers have similar structures or similar collision cross sections, it would be very difficult or impossible to resolve the isomers in ion mobility.

In this article, we report a detailed study of the isomers of Au_7^- and Au_8^- using Ar and O_2 -tagging, O_2 -titration, and isoelectronic atom substitution by Cu and Ag. We show that even for these very small clusters their structural isomers have not been fully understood. Both clusters have been suggested to have multiple isomers in our previous PES study, but not definitively identified.¹⁹ Here we show that there are two energetically and structurally close isomers for each cluster. In particular, we find a *dangling Au atom isomer* for Au_7^- , which is always populated in the cluster beam but has not been recognized. The relative stability of this isomer is found to vary with Cu or Ag substitution. Using O_2 -titration, we are able to obtain isomer-specific photoelectron spectrum of Au_8^- . The global minima and the low-lying structures of Au_7^- , Au_8^- , and MAu_n^- ($M=\text{Ag}, \text{Cu}$; $n=6, 7$) are obtained using basin-hopping searches^{36–39} and their computed densities of states (DOS) are used to compare with the PES data.

II. METHODS

A. PES EXPERIMENT

The experiment was carried with a magnetic bottle PES apparatus equipped with a laser vaporization cluster source, details of which has been reported elsewhere.⁴⁰ A gold disk target (or a gold target doped with Ag or Cu) was vaporized by a pulsed laser to generate a plasma inside a cluster nozzle with a large waiting room. A high-pressure helium carrier gas pulse was delivered to the nozzle simultaneously, cooling the plasma and initiating nucleation. Clusters formed inside the nozzle were entrained in the helium carrier gas and underwent a supersonic expansion for further cooling. After a skimmer, anions from the collimated cluster beam were extracted perpendicularly into a time-of-flight mass spectrometer. Clusters of interest were selected by a mass gate and decelerated before being photodetached by a 193 nm (6.424 eV) laser beam from an ArF excimer laser. Photoelectrons were collected by a magnetic bottle at nearly 100% efficiency into a 3.5-m-long electron flight tube for kinetic energy analyses. The photoelectron kinetic energies were calibrated by the known spectra of Au^- and subtracted from the photon energies to obtain the reported electron binding energy spectra. The electron kinetic energy (E_k) resolution of our apparatus is $\Delta E_k/E_k \sim 2.5\%$, i.e., ~ 25 meV for 1 eV electrons.

As shown previously,^{41,42} by carefully controlling the residence time of the clusters in the nozzle, relatively cold clusters can be produced from our laser vaporization supersonic cluster source. The cooling effects have been confirmed recently by the observation of molecular complexes of gold cluster anions with Ar and O_2 .^{22,28,31,43} In the present study, the Au_7Ar_x^- complexes were produced using a helium carrier gas seeded with 5% Ar. For the O_2 -tagging experiment, a 0.5% O_2/He carrier gas was used. For the O_2 -titration experiment for Au_8^- , a 25-mm-long and 6 mm diameter stainless steel reactor was added to the cluster nozzle. The

exit of the reactor was reduced to 3 mm diameter to enhance the reaction time. A hole was drilled in the middle of the reactor for the delivery of reactive gases. In the current study, a 0.5% O_2/He reactive gas was pulsed into the reactor for the titration experiment.

B. Theoretical calculations

The structural searches were done using the basin-hopping global minimum search technique coupled with DFT calculations for geometry optimization. Independent searches were performed using basin-hopping programs written by Wei Huang and the University of Nebraska-Lincoln (UNL) group; generalized gradient approximation in the Perdue–Burke–Ernzerhof (PBE) functional form⁴⁴ was chosen in both searches. Several randomly selected initial structures were used for the basin-hopping searches, all lead to consistent sets of low-lying isomers for each cluster anion. The top ten lowest-lying isomers were reoptimized using the PBE0/CRENBL *hybrid* functional/basis set, as implemented in the NWCHEM 5.1.1 software package.^{45,46} Lastly, relative energies of the top four lowest-lying isomers are computed using the M06-L functional^{23,24} and CRENBL basis set (with inclusion of spin-orbit effects). The results are presented in Figs. S1 and S2 and Tables S1 and S2 of Ref. 47.

To compare with the measured PES spectra, the first vertical detachment energies (VDEs) of the anion clusters were computed (at PBE0/CRENBL level of theory implemented in the NWCHEM 5.1.1, which includes the spin-orbit effects). The binding energies of deeper orbitals were then added to the first VDE to give VDEs for the excited states. Each VDE was fitted with a Gaussian of width 0.035 eV to yield the simulated DOS spectra.

III. RESULTS AND DISCUSSION

The photoelectron spectra of Au_n^- ($n=7, 8$) and MAu_n^- ($M=\text{Ag}, \text{Cu}$; $n=6, 7$) along with the corresponding simulated DOS spectra are presented in Figs. 1–4, respectively. The theoretical and experimental VDEs are compared in Table I.

Different anion isomers have different charge-induced *intermolecular interactions* with Ar.⁴³ Thus, the relative populations of different isomers can change in the cluster Ar complexes.²² Figure 1(a) shows that the relative intensities of the second peak (X') and several other peaks in the spectra of Au_7Ar^- (blue curve) are slightly reduced as compared to those of pure Au_7^- (red curve), indicating that these peaks likely come from a different (minor) isomer, whose interaction with Ar is weaker than that between the major isomer of Au_7^- and Ar. Furthermore, Au_7^- does not react with O_2 . However, we found that O_2 can physisorb onto Au_7^- , providing the possibility for O_2 -tagging.²⁸ Indeed, we see that the PES spectra of $\text{Au}_7(\text{O}_2)^-$ [Fig. 1(b)] and Au_7Ar^- are very similar. The observed differences between the PES spectra of Au_7^- and Ar/ O_2 -tagged Au_7^- are very small; the observation provides experimental hints that there are more than one isomer in the cluster beam.

To provide further evidence about the isomers of Au_7^- , we substituted one Au atom by a Ag or Cu atom. These isoelectronic substitutions can alter the relative stabilities of




FIG. 1. The 193 nm (6.424 eV) photoelectron spectra of (a) Au_7^- and Au_7Ar^- using a He carrier gas seeded with 1%–3% Ar and (b) Au_7^- and Au_7O_2^- using a He carrier gas seeded with 0.5% O_2 .

the isomers, thereby their *relative populations* in the cluster beams. Indeed, the PES spectra of AgAu_6^- [Fig. 2(b)] and CuAu_6^- [Fig. 2(c)] show remarkable similarities to that of undoped Au_7^- , except that the relative intensities of different peaks are changed. In particular, the relative intensity of the X' peak increased substantially, while those of the X and A peaks decreased. The A peak of AgAu_6^- is overlapped with the A' peak [Fig. 2(b)], but it is clear that the relative ratios of the X and A peaks are unchanged, suggesting that they come from one isomer, and this isomer is similar to the main isomer of Au_7^- . The X' and A' peaks increased in both the spectra of AgAu_6^- and CuAu_6^- proportionally, and they are similar to the X' and A' peaks in Au_7^- , suggesting that this isomer becomes the *dominant species* in the doped clusters.

To identify the two isomers, we performed basin-hopping global minimum searches combined with DFT calculations on Au_7^- , AgAu_6^- , and CuAu_6^- from randomly generated initial structures. It should be pointed out that two independent basin-hopping searches^{36,37} on Au_7^- were per-




FIG. 2. Left panel: 193 nm experimental photoelectron spectra of (a) Au_7^- , (b) AgAu_6^- , and (c) CuAu_6^- . Right panel: Structures and simulated DOS spectra of isomers I and II for (d) Au_7^- , (e) AgAu_6^- , and (f) CuAu_6^- .




FIG. 3. Photoelectron spectra of Au_8^- . (a) Using pure He carrier gas; (b) using a 5% O_2/He reactant gas with the flow tube reactor; (c) the spectrum of the D_{4h} isomer obtained by subtracting (d) from (b); and (d) the spectrum of the C_{2v} isomer obtained by subtracting (b) from (a).

formed in the current study, one by a program written by one of the coauthors (W. H.) and another by the UNL group. A dangling Au atom isomer of Au_7^- was found independently using both programs. The basin-hopping searches of the Au/Ag and Au/Cu binary clusters were performed solely by the UNL group.^{38,39} The top ten low-lying isomers were re-optimized and relative energies of four low-lying isomers are presented in Fig. S1.⁴⁷ Except CuAu_6^- , we found that the 2D planar isomers are appreciably lower in energy than the 3D isomers (Fig. S1).⁴⁷ The lowest-energy isomer of CuAu_6^- has a 3D structure. However, the computed DOS spectrum




FIG. 4. Left panel: 193 nm photoelectron spectra of (a) Au_8^- , (b) AgAu_7^- , and (c) CuAu_7^- . Right panel: The structures and simulated DOS spectra of isomers I and II for (d) Au_8^- , (e) AgAu_7^- , and (f) CuAu_7^- .

TABLE I. The measured VDEs compared to calculated VDEs for the isomers of the pure gold clusters Au_7^- and Au_8^- , and the doped clusters MAu_6^- and MAu_7^- ($M=\text{Ag}, \text{Cu}$). All energies are in electron volts.

	VDE (eV)	
	Expt. ^a	Theor. ^b
Au_7^- (I)	3.46(2) ^c	3.24
Au_7^- (II)	3.92(3)	3.61
AgAu_6^- (I)	3.45(4)	3.22
AgAu_6^- (II)	3.94(3)	3.62
CuAu_6^- (I)	3.40(4)	3.24
CuAu_6^- (II)	3.94(3)	3.62
Au_8^- (I, D_{4h})	2.79(2) ^c	2.69
Au_8^- (II, C_{2v})	2.91(4)	2.82
AgAu_7^- (I)	2.69(4)	2.61
AgAu_7^- (II)	3.06(4)	2.96
CuAu_7^- (I)	2.83(4)	2.71
CuAu_7^- (II)	3.07(4)	2.97

^aNumbers in parentheses represent the uncertainty in the last digit.

^bTheoretical VDE is always smaller than the experimental VDE by 0.1–0.3 eV when spin-orbit effects are included in PBE0/CRENBL level calculation.

^cTaken from Ref. 19.

[Fig. S1(i)] (Ref. 47) of this 3D isomer is markedly different from the measured PES spectrum, and thus can be ruled out.

The lowest-energy isomer of Au_7^- is the same as reported before.^{10,18,19} The low-lying isomer of Au_7^- , a dangling Au atom structure (coordinates of this isomer is given in Table S1),⁴⁷ can be viewed by simply attaching the extra atom to an apex site of the very stable D_{3h} Au_6^- cluster. It is remarkable that this isomer was missed in all previous studies on Au_7^- (note that the isomer 7B reported in Ref. 19 is not a local minimum based on the PBE0/CRENBL calculation). The two lowest-lying 2D planar isomers of AgAu_6^- and CuAu_6^- have nearly the same structures as those of Au_7^- , except that the dangling Au atom structure becomes the lowest-energy 2D structure rather than the second lowest-energy 2D structure (Fig. S1).⁴⁷ This change in relative stabilities between the two lowest-lying isomers corroborates with the change in relative populations in the cluster beams, as demonstrated by the substantial change in the relative intensity between the X' peak and the X peak [Figs. 2(a)–2(c)].

In MAu_6^- ($M=\text{Ag}, \text{Cu}$), the Ag or Cu atom seems to prefer the site with *more coordination* in both isomers and to stay away from the dangling Au atom [Figs. 2(e) and 2(f) and Table S1 (Ref. 47)]. To compare with the experimental data, we computed the DOS spectra by including the relativistic and spin-orbit effects for several lowest-lying isomers. As shown in Fig. 2, the simulated DOS spectra for the two lowest-lying 2D isomers of Au_7^- , AgAu_6^- , and CuAu_6^- are in quantitative agreement with the experimental data, providing considerable credence for the identified isomers for these clusters.

It is interesting to understand why the difference between the spectra of Au_7^- and Au_7Ar^- is small compared to the difference observed previously between the spectra of Au_{12}^- and $\text{Au}_{12}\text{Ar}^-$.²² This is due to the fact that the two

isomers of Au_{12}^- are 2D and 3D,¹⁰ respectively, and, therefore, have very different intermolecular interactions with Ar, while both isomers of Au_7^- are 2D and have similar intermolecular interactions with Ar.

We also attempted Ar-tagging on Au_8^- , but the spectra of Au_8Ar^- and Au_8^- are nearly identical and cannot be used to distinguish contributions from different isomers. Au_8^- is reactive with O_2 , providing an opportunity to carry out O_2 -titration.^{27,28} We have built a fast flow cluster reactor, which consists of a 25-mm-long and 6 mm diameter stainless steel tube attached to the cluster source nozzle. Reactant gases (O_2 here) can be introduced through a hole drilled in the middle of the stainless steel tube. A cap with a 3 mm hole is installed at the exit of the tube to increase the residence time of the reactant. By using a 5% O_2/He reactant gas, we obtained the Au_8^- spectrum, as shown in Fig. 3(b). This spectrum is quite different from that using pure He carrier gas [Fig. 3(a)] that we reported previously.¹⁹ Specifically, the relative intensities of the X' , A' , and B' peaks decreased dramatically, suggesting that they come from an isomer that has been titrated out of the cluster beam. The ground state of Au_8^- is known to be of a D_{4h} structure and its low-lying isomer is a C_{2v} structure [Fig. 4(d)].^{10,19} Clearly, the low-lying C_{2v} isomer, which corresponds to the X' , A' and B' peaks, is titrated out of the cluster beam. Since Fig. 3(b) contains very little contribution from the C_{2v} isomer, this spectrum is subtracted from Fig. 3(a) to yield the isomer-specific spectrum for the C_{2v} isomer, as shown in Fig. 3(d).⁴⁸ The spectrum in Fig. 3(d) is then subtracted from Fig. 3(b) to yield the isomer-specific spectrum for the D_{4h} structure [Fig. 3(c)] by appropriate normalization.

The photoelectron spectra of Ag/Cu substituted Au_8^- are shown in Figs. 4(b) and 4(c). The peak positions of AgAu_7^- and CuAu_7^- are almost the same as that of Au_8^- , suggesting that the same isomers are present in the spectra of the substituted clusters. However, the relative intensities are changed: the X' , A' , and B' peaks become weaker in the spectrum of AgAu_7^- [Fig. 4(b)], implying that the C_{2v} -type isomer in AgAu_7^- may become less stable. The same peaks become dominant in the spectrum of CuAu_7^- [Fig. 4(c)], suggesting that the C_{2v} -type isomer may become the global minimum in this system. The weak peak labeled with * in Fig. 4(c) may arise from an unidentified impurity or another minor isomer.

We also performed independent basin-hopping searches for Au_8^- , AgAu_7^- , and CuAu_7^- . The two lowest-lying structures of each species are shown in Figs. 4(d)–4(f), respectively (coordinates are given in Table S2),⁴⁷ and relative energies of four low-lying isomers are presented in Fig. S2.⁴⁷ The DFT calculation suggests that the D_{4h} and C_{2v} isomers of Au_8^- are isoenergetic [Figs. S2(a) and S3(b)] (Ref. 47) and both are candidates of the lowest-energy clusters.^{10,19} The simulated DOS spectra of the two isomers are in excellent agreement with the isomer-specific PES spectra shown in Figs. 3(c) and 3(d), respectively. The next low-lying isomer is much higher in energy than the D_{4h} and C_{2v} isomers [Fig. S2(c)].⁴⁷

The two lowest-lying structures of AgAu_7^- and CuAu_7^- are found indeed to be similar to those of Au_8^- . Again, we

found that the Ag and Cu atoms prefer high coordination sites in AgAu_7^- and CuAu_7^- . The simulated DOS spectra for the two isomers of AgAu_7^- and CuAu_7^- are also in very good agreement with the experimental data, lending additional credence to the structures identified for the substituted clusters. Moreover, the change in the relative stabilities of the isomers of CuAu_7^- [Figs. S2(i) and S2(j)] (Ref. 47) is consistent with the major change in relative populations in the cluster beams as demonstrated by the substantial change in the relative intensity of the X' peak versus the X peak [Figs. 4(a) and 4(c)]. However, the change in the relative stabilities of the isomers of AgAu_7^- [Figs. S2(e) and S2(f)] (Ref. 47) is inconsistent with the relatively small change in relative populations in the cluster beams. Perhaps much larger basis sets than the CRENL or higher-level theories than DFT are needed to resolve this inconsistency.

IV. CONCLUSION

In conclusion, we report a detailed investigation of the structures and isomers of Au_7^- and Au_8^- using a combination of experimental techniques (Ar-tagging, O_2 -titration, and iso-electronic substitution) in conjunction with basin-hopping global minimum searches. A new isomer is identified for Au_7^- , which consists of a triangular Au_6 unit with a terminal Au atom. For Au_8^- , we found that O_2 -titration can be used to titrate out the second lowest-energy isomer to yield isomer-specific PES spectra. The Ag and Cu substituted Au_7^- and Au_8^- clusters are shown to possess similar structures and isomers as the parent clusters and the Ag and Cu dopant atoms are found to prefer high coordination sites. The current study reveals the structural diversity for even relatively small Au clusters and demonstrates that well-designed PES experiments in combination with *ab initio* calculations are highly valuable to elucidate the structures and energetics of nano-clusters.

ACKNOWLEDGMENTS

The experimental work was supported by the U.S. National Science Foundation (Grant No. CHE-0749496). The theoretical work done by W.H. was performed with the supercomputers at the EMSL Molecular Computing Facility of Pacific Northwest National Lab. W.H. thanks Dr. Niranjana Govind, High-Performance Computing Center in EMSL, and the NWCHEM developer team for invaluable help in developing the basin-hopping program. The theoretical work done at Nebraska was supported by grants from the National Science Foundation (Grant No. DMR-0820521), the Nebraska Research Initiative, and the University of Nebraska Holland Computing Center.

¹M. Haruta, *Catal. Today* **36**, 153 (1997).

²P. Pyykkö, *Chem. Soc. Rev.* **37**, 1967 (2008).

³H. Häkkinen, *Chem. Soc. Rev.* **37**, 1847 (2008).

⁴P. Pyykkö, *Nat. Nanotechnol.* **2**, 273 (2007).

⁵R. M. Olson and M. S. Gordon, *J. Chem. Phys.* **126**, 214310 (2007).

⁶P. Koskinen, H. Häkkinen, B. Huber, B. v. Issendorff, and M. Moseler, *Phys. Rev. Lett.* **98**, 015701 (2007).

⁷P. Pyykkö, *Inorg. Chim. Acta* **358**, 4113 (2005).

⁸A. A. Herzing, C. J. Kiely, A. F. Carley, P. Landon, and G. J. Hutchings, *Science* **321**, 1331 (2008).

⁹K. J. Taylor, C. L. Pettiettehall, O. Cheshnovsky, and R. E. Smalley, *J. Chem. Phys.* **96**, 3319 (1992).

¹⁰F. Furche, R. Ahlrichs, P. Weis, C. Jacob, S. Gilb, T. Bierweiler, and M. M. Kappes, *J. Chem. Phys.* **117**, 6982 (2002).

¹¹P. Weis, *Int. J. Mass Spectrom.* **245**, 1 (2005).

¹²A. Fielicke, A. Kirilyuk, C. Ratsch, J. Behler, M. Scheffler, G. von Helden, and G. Meijer, *Phys. Rev. Lett.* **93**, 023401 (2004).

¹³P. Gruene, D. M. Rayner, B. Redlich, A. F. G. van der Meer, J. T. Lyon, G. Meijer, and A. Fielicke, *Science* **321**, 674 (2008).

¹⁴X. Xing, B. Yoon, U. Landman, and J. H. Parks, *Phys. Rev. B* **74**, 165423 (2006).

¹⁵P. Pyykkö, *Chem. Rev. (Washington, D.C.)* **88**, 563 (1988).

¹⁶P. Pyykkö, *Angew. Chem., Int. Ed.* **43**, 4412 (2004).

¹⁷U. Landman, *Proc. Natl. Acad. Sci. U.S.A.* **102**, 6671 (2005).

¹⁸H. Häkkinen, M. Moseler, and U. Landman, *Phys. Rev. Lett.* **89**, 033401 (2002).

¹⁹H. Häkkinen, B. Yoon, U. Landman, X. Li, H. J. Zhai, and L. S. Wang, *J. Phys. Chem. A* **107**, 6168 (2003).

²⁰S. Gilb, K. Jacobsen, D. Schooss, F. Furche, R. Ahlrichs, and M. M. Kappes, *J. Chem. Phys.* **121**, 4619 (2004).

²¹M. P. Johansson, A. Lechtken, D. Schooss, M. M. Kappes, and F. Furche, *Phys. Rev. A* **77**, 053202 (2008).

²²W. Huang and L. S. Wang, *Phys. Rev. Lett.* **102**, 153401 (2009).

²³L. Ferrighi, B. Hammer, and G. K. H. Madsen, *J. Am. Chem. Soc.* **131**, 10605 (2009).

²⁴M. Mantina, R. Valero, and D. G. Truhlar, *J. Chem. Phys.* **131**, 064706 (2009).

²⁵J. Li, X. Li, H. J. Zhai, and L. S. Wang, *Science* **299**, 864 (2003).

²⁶S. Bulusu, X. Li, L. S. Wang, and X. C. Zeng, *Proc. Natl. Acad. Sci. U.S.A.* **103**, 8326 (2006).

²⁷A. Lechtken, C. Neiss, M. M. Kappes, and D. Schooss, *Phys. Chem. Chem. Phys.* **11**, 4344 (2009).

²⁸W. Huang, S. Bulusu, R. Pal, X. C. Zeng, and L. S. Wang, *ACS Nano* **3**, 1225 (2009).

²⁹M. Walter and H. Häkkinen, *Phys. Chem. Chem. Phys.* **8**, 5407 (2006).

³⁰D. Y. Zubarev and A. I. Boldyrev, *J. Phys. Chem. A* **113**, 866 (2009).

³¹W. Huang and L. S. Wang, *Phys. Chem. Chem. Phys.* **11**, 2663 (2009).

³²R. M. Olson, S. Varganov, M. S. Gordon, H. Metiu, S. Chretien, P. Piecuch, K. Kowalski, S. A. Kucharski, and M. Musial, *J. Am. Chem. Soc.* **127**, 1049 (2005).

³³M. Diefenbach and K. S. Kim, *J. Phys. Chem. B* **110**, 21639 (2006).

³⁴M. B. Knickelbein and W. J. C. Menezes, *Chem. Phys. Lett.* **184**, 433 (1991).

³⁵M. B. Knickelbein and S. Yang, *J. Chem. Phys.* **93**, 1476 (1990).

³⁶D. J. Wales and H. A. Scheraga, *Science* **285**, 1368 (1999).

³⁷S. Yoo and X. C. Zeng, *Angew. Chem., Int. Ed.* **44**, 1491 (2005).

³⁸L. M. Wang, S. Bulusu, H. J. Zhai, X. C. Zeng, and L. S. Wang, *Angew. Chem., Int. Ed.* **46**, 2915 (2007).

³⁹L. M. Wang, R. Pal, W. Huang, X. C. Zeng, and L. S. Wang, *J. Chem. Phys.* **130**, 051101 (2009).

⁴⁰L. S. Wang, H. S. Cheng, and J. W. Fan, *J. Chem. Phys.* **102**, 9480 (1995).

⁴¹J. Akola, M. Manninen, H. Häkkinen, U. Landman, X. Li, and L. S. Wang, *Phys. Rev. B* **60**, R11297 (1999).

⁴²L. S. Wang and X. Li, in *Temperature Effects in Anion Photoelectron Spectroscopy of Metal Clusters in Clusters and Nanostructure Interfaces*, edited by P. Jena, S. N. Khanna, and B. K. Rao (World Scientific, River Edge, 2000), p. 293.

⁴³Y. Gao, W. Huang, J. Woodford, L. S. Wang, and X. C. Zeng, *J. Am. Chem. Soc.* **131**, 9484 (2009).

⁴⁴J. P. Perdew, K. Burke, and M. Ernzerhof, *Phys. Rev. Lett.* **77**, 3865 (1996).

⁴⁵R. A. Kendall, E. Aprà, D. E. Bernholdt, E. J. Bylaska, M. Dupuis, G. I. Fann, R. J. Harrison, J. Ju, J. A. Nichols, J. Nieplocha, T. P. Straatsma, T. L. Windus, and A. Wong, *Comput. Phys. Commun.* **128**, 260 (2000).

⁴⁶E. J. Bylaska *et al.*, Pacific Northwest National Laboratory, Richland, Washington 99352-0999, USA (2009).

⁴⁷See supplementary material at <http://dx.doi.org/10.1063/1.3299292> for more information on relative energies, structures and simulated PES of four lowest-lying isomers of each cluster, and Cartesian coordinates of the two lowest-lying isomers of each cluster.

⁴⁸Because the spectrum in Fig. 3(b) still contains small contributions from bands X', A', and B', the subtraction method is a very approximate way to yield isomer-specific spectra.