University of Nebraska - Lincoln

DigitalCommons@University of Nebraska - Lincoln

Mechanical & Materials Engineering Faculty
Publications

Mechanical & Materials Engineering,
Department of

2021

Assembly of Close-Packed Ferroelectric Polymer Nanowires via Interface-Epitaxy with ReS₂

Dawei Li

University of Nebraska-Lincoln

Shuo Sun

University of Nebraska-Lincoln, ssun8@unl.edu

Kun Wang

University of Nebraska-Lincoln, kun.wang@huskers.unl.edu

Zahra Ahmadi

University of Nebraska-Lincoln, zahmadi2@unl.edu

Jeffrey E. Shield

University of Nebraska - Lincoln, jshield@unl.edu

See next page for additional authors

Follow this and additional works at: <https://digitalcommons.unl.edu/mechengfacpub>

Part of the [Mechanics of Materials Commons](#), [Nanoscience and Nanotechnology Commons](#), [Other Engineering Science and Materials Commons](#), and the [Other Mechanical Engineering Commons](#)

Li, Dawei; Sun, Shuo; Wang, Kun; Ahmadi, Zahra; Shield, Jeffrey E.; Ducharme, Stephen; and Hong, Xia, "Assembly of Close-Packed Ferroelectric Polymer Nanowires via Interface-Epitaxy with ReS₂" (2021).

Mechanical & Materials Engineering Faculty Publications. 621.

<https://digitalcommons.unl.edu/mechengfacpub/621>

This Article is brought to you for free and open access by the Mechanical & Materials Engineering, Department of at DigitalCommons@University of Nebraska - Lincoln. It has been accepted for inclusion in Mechanical & Materials Engineering Faculty Publications by an authorized administrator of DigitalCommons@University of Nebraska - Lincoln.

Authors

Dawei Li, Shuo Sun, Kun Wang, Zahra Ahmadi, Jeffrey E. Shield, Stephen Ducharme, and Xia Hong

Assembly of Close-Packed Ferroelectric Polymer Nanowires via Interface-Epitaxy with ReS_2

Dawei Li,¹ Shuo Sun,¹ Kun Wang,¹ Zahra Ahmadi,²
Jeffrey E. Shield,² Stephen Ducharme,¹ and Xia Hong¹

¹ Department of Physics and Astronomy & Nebraska Center for Materials and Nanoscience, University of Nebraska-Lincoln, Lincoln, Nebraska 68588-0299, USA

² Department of Mechanical and Materials Engineering, University of Nebraska-Lincoln, Lincoln, NE 68588-0526, USA

Correspondence — X. Hong, email xia.hong@unl.edu

Abstract

The flexible, transparent, and low-weight nature of ferroelectric polymers makes them promising for wearable electronic and optical applications. To reach the full potential of the polarization-enabled device functionalities, large-scale fabrication of polymer thin films with well-controlled polar directions is called for, which remains a central challenge. The widely exploited Langmuir–Blodgett, spin-coating, and electrospinning methods only yield polymorphous or polycrystalline films, where the net polarization is compromised. Here, an easily scalable approach is reported to achieve poly(vinylidene fluoride-trifluoroethylene) P(VDF-TrFE) thin films composed of close-packed crystalline nanowires via interface-epitaxy with $1\text{T}'\text{-ReS}_2$. Upon controlled thermal treatment, uniform P(VDF-TrFE) films restructure into about 10 and 35 nm-wide (010)-oriented nanowires

Published in *Advanced Materials* 33 (2021), 2100214.

DOI: 10.1002/adma.202100214

Copyright © 2021 Wiley-VCH GmbH. Used by permission.

Submitted January 10, 2021; revised March 30, 2021; published June 1, 2021.

that are crystallographically aligned with the underlying ReS_2 , as revealed by high-resolution transmission electron microscopy. Piezoresponse force microscopy studies confirm the out-of-plane polar axis of the nanowire films and reveal coercive voltages as low as 0.1 V. Reversing the polarization can induce a conductance switching ratio of $>10^8$ in bilayer ReS_2 , over six orders of magnitude higher than that achieved by an untreated polymer gate. This study points to a cost-effective route to large-scale processing of high-performance ferroelectric polymer thin films for flexible energy-efficient nanoelectronics.

Keywords: interface epitaxy, van der Waals heterostructures, ReS_2 , ferroelectric polymers, crystalline nanowires

1. Introduction

The flexible, transparent, and low-weight nature of ferroelectric polymers makes them a promising material platform for developing wearable electronic and optical applications.^[1–5] Leveraging their large, nanoscale controllable polarization, extensive research has been carried out on integrating poly(vinylidene fluoride-trifluoroethylene) P(VDF-TrFE) thin films with 2D van der Waals (vdW) materials for constructing a range of novel nanodevices,^[6,7] including nonvolatile memories,^[8–11] negative-capacitance field-effect transistors (FETs),^[12,13] neuromorphic memristors,^[14] and reconfigurable diodes.^[10,11,15,16] One of the central challenges for technological implementation of these polarization-enabled device concepts is the lack of viable fabrication techniques for achieving large-scale crystalline polymer films with well-defined polarization direction. The widely exploited Langmuir–Blodgett (LB),^[1,2,4,10,11] spin coating,^[5,8,9,12–17] and electrospinning^[18,19] methods only yield polymorphous or polycrystalline films with compromised net polarization, which significantly limit the device performance. In this work, we report an easily scalable approach for fabricating highly ordered crystalline P(VDF-TrFE) nanowire (P-NW) films, which leverages the interfacial epitaxial relation with an anisotropic vdW material, $1\text{T}'\text{-ReS}_2$. Upon controlled thermal treatment, uniform LB films self-assemble into close-packed NWs that are crystallographically aligned with the underlying ReS_2 with out-of-plane polar axis (**Figure 1a**). Compared with the pristine LB films, the P-NW films can lead to over six orders of magnitude higher ferroelectric field effect modulation in bilayer ReS_2 FET devices,

Figure 1. P-NW film on ReS₂. a) Sample schematic. b) AFM topography image of a P-NW film formed on 1L ReS₂. Upper inset: AFM image of the initial 9 ML LB film. Lower inset: polarization-resolved Raman signal of mode V of the 1L ReS₂. c) Optical image of two perpendicularly stacked 1L ReS₂ flakes (top), and the polar plots of parallel polarization-resolved Raman signal of mode V for the T-1L (red) and B-1L (blue) ReS₂ (bottom). d) AFM image of the boxed area in (c). The crystalline orientations of ReS₂ are labeled.

and the coercive voltage can be as low as 0.1 V. Our approach offers a cost-effective strategy for achieving large-scale highly crystalline P(VDF-TrFE) thin films in the vdW heterostructure form, paving the path for their implementation in wearable energy-efficient nanoelectronics.

2. Results and Discussion

Using the horizontal LB deposition technique,^[2] we deposited 1–9 monolayer (ML) P(VDF-TrFE) thin films on ReS₂ (Experimental Section). Figure 1b upper inset shows the atomic force microscopy (AFM) image of a 9 ML LB film prepared on a mechanically exfoliated single-layer (1L) ReS₂ flake on SiO₂ substrate (Figure S1, Supporting Information). After controlled thermal annealing, the initially smooth and uniform film reconstructs into well aligned, close-packed NWs with an average width of 35 nm (Figure 1b; Figure S2, Supporting Information), which are perpendicular to the Re chain direction (b_R -axis). Figure 1c shows a sample prepared on two perpendicularly stacked 1L ReS₂. On the 1L ReS₂ regions, the NW orientations are perpendicular to the b_R -axis of the underlying ReS₂, which is in sharp contrast to the randomly oriented nanostructures formed on the SiO₂ substrate (Figure 1d).^[20,21] Close to the edges of ReS₂, the NWs extend onto SiO₂, forming wire bundles that are perpendicular to each other. Interestingly, such a competing effect of NW orientation is not observed on the stacked bilayer ReS₂ region. Instead, the NW orientation is solely determined by the top layer (T-1L) ReS₂, forming a sharp interface with those on the bottom layer (B-1L). These results clearly point to an extremely short-ranged interfacial interaction between the P-NW and ReS₂. It is thus expected that the thickness of ReS₂ is not a relevant factor for the NW formation. Indeed, we have achieved reliable fabrication of P-NWs on 1L, 2L, and few-layer ReS₂ flakes (Figure S3, Supporting Information), as well as bulk ReS₂ samples. **Figure 2a** shows the P-NW film prepared on a bulk ReS₂ single crystal, with the dimension approaching the centimeter scale, confirming the scalability of this fabrication approach.

To understand the role of the base layer in the P-NW formation, we prepared P(VDF-TrFE) samples on five other 2D vdW materials using identical fabrication methods (Figure S4, Supporting Information). The samples prepared on the isotropic 2H-MoS₂, graphene, and α -In₂Se₃

Figure 2. Structural properties of P-NW on ReS_2 . a) AFM topography image of a P-NW film on bulk ReS_2 . Lower inset: optical image of the sample laid on a SiO_2 substrate. The dotted lines outline the ReS_2 single crystal. b) Cross-sectional TEM image of a sample prepared on bulk ReS_2 . c,d) Fast Fourier transform results for ReS_2 (c) and P-NW (d) taken from the boxed areas in (b). e) High-resolution TEM image of a P-NW on ReS_2 . f) Expanded view of the boxed area in (e) superimposed with the atomic arrangements of ReS_2 and (010) P(VDF-TrFE). The interface between P(VDF-TrFE) and ReS_2 in (e) and (f) is marked by the dashed lines. g) Schematic illustration of the epitaxial relation between P(VDF-TrFE) and ReS_2 . The dashed lines mark the unit cells for P(VDF-TrFE) and ReS_2 . The laboratory coordinate system and crystal-line orientations of P(VDF-TrFE) and ReS_2 are labeled.

form randomly distributed rice-like nanograins, similar to previous reports on graphene.^[9] Surprisingly, samples prepared on anisotropic black phosphorus and TiS_3 also show isotropic nanograin distribution, indicating that the lattice anisotropy alone is not sufficient to align the P-NW assembly. To probe the details of the interfacial crystalline registration, we performed transmission electron microscopy (TEM) studies on a sample prepared on bulk ReS_2 . Figure 2b shows the cross-sectional TEM image of two close-packed NWs. Fourier transform analysis of the image reveals clear diffraction spots for ReS_2 (Figure 2c) and P-NWs (Figure 2d), pointing to (010)-orientated P-NWs with high crystallinity. The high-resolution TEM image resolves the layered structure of one P-NW (Figure 2e) with interlayer spacing of $2.48 \pm 0.01 \text{ \AA}$. This value agrees closely with half of the b_p -axis lattice parameter of orthorhombic P(VDF-TrFE) (70/30) ($b_p = 5.12 \text{ \AA}$),^[22] confirming the (010)-orientation (Figure S5, Supporting Information). Mapping the atomic arrangements on the TEM image shows that the in-plane polymer chain (c_p -axis) is aligned with the Re-chain direction of ReS_2 (b_R -axis) (Figure 2f).

As illustrated in Figure 2g, in this configuration, there exists a clear epitaxial lattice relation between these two materials. In the y - z plane, the distance between five neighboring polymer chains ($2a_p \approx 17.16 \text{ \AA}$) matches well with three monomer distance of ReS_2 ($\approx 17.19 \text{ \AA}$). In the x - z plane, the extension of five P(VDF-TrFE) monomers ($5c_p \approx 12.8 \text{ \AA}$) closely match the distance between monomer units of ReS_2 ($2b_R \approx 12.9 \text{ \AA}$). As the interlayer interaction in orthorhombic P(VDF-TrFE) is also vdW type, we conclude that the close lattice match can enable the formation of an epitaxial vdW heterointerface between the P-NWs and ReS_2 , with $b_p \parallel c_R$, $c_p \parallel b_R$, and $a_p \perp b_R$. The moderate in-plane tensile strain (0.2% along a_p and 0.8% along c_p) is also consistent with the slightly compressed interlayer spacing deduced from the TEM measurements. This scenario naturally explains why P(VDF-TrFE) on black phosphorus and TiS_3 only forms randomly distributed nanograins: the P-NW orientation on ReS_2 is guided by the epitaxial-type interfacial atomic registry, rather than merely the lattice symmetry. Unlike previous P-NW studies exploiting nanoimprinting^[3,23] and AFM tip imposed mechanical annealing,^[24] our approach leverages the crystalline interaction with the ReS_2 interface to guide the NW self-assembly, which yields close-packed NWs forming large-scale continuous films.

We characterized the ferroelectric properties of the P-NW film via vertical and lateral piezoresponse force microscopy (PFM). **Figure 3a** shows the vertical PFM (V-PFM) switching hysteresis taken on a sample formed from 9 ML P(VDF-TrFE). The coercive voltages are approximately +0.6 and −0.8 V for the polarization up (P_{up}) and down (P_{down}) states, respectively. The corresponding coercive field (E_c) is about 0.05 V nm^{-1} or less, which is significantly lower than the films prepared by the LB^[25,26] method ($0.1\text{--}1 \text{ V nm}^{-1}$) and becomes comparable with those of the oxide ferroelectrics.^[27] Such low E_c can be attributed to the out-of-plane polar orientation of the P-NW films. Unlike the polycrystalline LB films, where the polarization points 30° away from the film normal,^[28] the P-NWs crystallize along the polar axis (Figure 2f), requiring a significantly reduced switching field due to the polar anisotropy. Figure 3b,c shows the V-PFM images taken on the stripe P_{up} and P_{down} domains written on the sample. The as-grown state is close to the uniformly polarized P_{up} state, similar as the LB films.^[29] The lateral PFM (L-PFM) signal on the same domain structure is close to the noise level for all three regions, with no appreciable dependence on the scanning angle (Figure S6, Supporting Information). This result indicates a lack of in-plane component of polarization, consistent with the out-of-plane polar axis of the (010) film. In contrast, annealed LB films typically crystallize in the (110) direction, which possesses intercorrelated in-plane and out-of-plane polarization.^[25,30]

The out-of-plane polarization and small coercive voltage make the P-NW films an ideal choice as ferroelectric gate for FET devices (Figure 3d). Figure 3e shows the source–drain current–voltage relation ($I_{\text{DS}}\text{--}V_{\text{DS}}$) of a 2L ReS₂ device at zero back-gate bias ($V_{\text{BG}} = 0 \text{ V}$), which corresponds to a channel conductivity switching ratio of 1.6×10^6 between the P_{up} and P_{down} states of the P-NW top-layer. Figure 3f compares the transfer characteristics ($I_{\text{DS}}\text{--}V_{\text{BG}}$) of a 2L ReS₂ device for both polarizations of the P-NW top-gate. At $V_{\text{BG}} = 30 \text{ V}$, the device shows a current switching ratio of 1.4×10^8 . Even high switching ratio is expected at the gate range of $V_{\text{BG}} = 15\text{--}30 \text{ V}$, where I_{D} is below the instrument resolution. In contrast, in a 2L ReS₂ device gated by untreated LB film, the highest current switching ratio is $\approx 1.2 \times 10^2$ (Figure 3f inset). The more than six orders of magnitude difference in the current switching ratio clearly illustrates the powerful gating capacity of highly crystalline P(VDF-TrFE) with out-of-plane polar axis.

Figure 3. Characterizations of P-NWs and P-NW/ReS₂ FETs. a) V-PFM hystereses of phase (top) and amplitude (bottom) responses taken on a P-NW film prepared from a 9 ML LB film. b,c) PFM phase (b) and amplitude (c) images of a domain structure patterned on a P-NW film. The lower panels show the V-PFM and L-PFM signal profiles along the dashed lines. d–f) Characterizations of 2L ReS₂ FETs with SiO₂ back-gate and P(VDF-TrFE) top-gate at room-temperature. d) Device schematic. e) I_{DS} versus V_{DS} at $V_{\text{BG}} = 0$ V for the uniformly polarized P_{down} and P_{up} states of the P-NW top-layer, with the corresponding PFM phase images shown as insets. The scale bars are 2 μm . f) I_{DS} versus V_{BG} for the P_{down} and P_{up} states of the P-NW top-gate. Inset: I_{DS} versus V_{BG} of a 2L ReS₂ device top-gated by 9 ML untreated LB film for both polarization states.

To understand the formation mechanism of the P-NWs, we performed in situ AFM imaging on 5 and 1 ML P(VDF-TrFE) films on ReS₂ during the thermal treatment (**Figure 4a**). The 5 ML LB film does not show obvious change in morphology till a transition temperature $T_1 = 120$ °C, upon which the continuous film starts to transform into a texture composed of short NW segments. At this stage, there are short NWs lying along both x - and y -directions, which are parallel and perpendicular to the b_R axis of ReS₂, respectively. Further heating the sample to $T_2 = 130$ °C, the texture quickly evolves into well aligned NWs, where the x -oriented NWs disappear (or reorient) and y -oriented NWs merge into longer wires. The resulting P-NW film is continuous and stable upon cooling.

For the 1 ML P(VDF-TrFE), the initial LB film does not have a uniform surface coverage on ReS₂ at room temperature. Upon heating, randomly bundled fine NWs gradually emerge within the textures above a lower $T_1 = 80$ °C. These fine NWs start to reorient along y -axis at $T_2 = 110$ °C, with the neighboring ones merging into wider and longer NWs. The straightening and merging of NWs continue until 120 °C. Further heating the sample to 130 °C does not change the NW width, while the smaller patches congregate into large NW bundles. Similar to the 5 ML sample, the film maintains similar surface morphology during cooling. The NW formation, on the other hand, is highly sensitive to the thermal annealing temperature, and the well structured NWs would melt and break into isolated droplets when the sample is heated above 140 °C (Figure S7, Supporting Information).

As shown in Figure 4b insets, the morphology of the P-NW film evolves from scattered big islands of NW bundles to homogeneous films with fewer and fewer vacant areas with increasing layer number of the initial LB film. For all samples, however, we have full coverage of P-NWs over the entire sample surface. For the 6 ML and thicker samples, the final film is uniformly covered by wide NWs with no vacant spots over a large scale of area. The width (w) of the NWs ranges from 33 to 37 nm with no appreciate layer number dependence (Figure 4b). For samples thinner than 6 ML, the seemingly vacant regions are actually fully covered by fine NWs (Figure 4c,d), which are also aligned along the same orientation. The height difference (Δh) between the surfaces of the wide NW and fine NW regions is about 7–8 nm, also independent of the layer number. Taking into account the thickness of the fine NWs, i.e., about 7 nm (Figure 2b), we estimate the height of the wide NWs to be about

Figure 4. Effects of temperature and LB film thickness. a) In situ AFM images of the surface morphology of 5 ML (top) and 1 ML (bottom) LB films on ReS_2 illustrating the P-NW formation process. The images do not correspond to the same sample area due to thermal drift of AFM. b) NW width w (left axis) and Δh (right axis) versus layer number of initial LB film, with AFM topography images of the corresponding P-NW films at room temperature (insets). The dashed lines serve as the guide to the eye. The crystalline orientations of ReS_2 are the same as in (a). c,d) Close-up AFM images taken on the (c) 3 ML and (d) 4 ML samples in the boxed areas in (b).

14–15 nm. We also measured the height of wide NWs directly on the 6 and 9 ML samples with respect to the pinholes, and obtained consistent results.

As shown in **Figure 5a**, the width of the fine NWs is about 10 nm. The PFM switching hystereses taken on the fine NW region reveal an ultralow coercive voltage of about ± 0.1 V (Figure 5b), corresponding to

Figure 5. Characterizations of fine P-NWs and NW formation mechanism. a) Close-up AFM topography image taken on the 1 ML sample in the boxed area in Figure 4b, with the height profile along the dashed line (bottom). b) V-PFM hystereses of phase (top) and amplitude (bottom) responses taken on the fine NW film in (a). c) Conductance versus T for a 1L ReS_2 device in the pristine state (black) and with (red) 9 ML LB film deposited on top. The conductance is normalized to the value at 70 °C (S_{norm}). Inset: optical image of the ReS_2 device coated with 9 ML LB film. d) S_{norm} versus T for a 1L ReS_2 device in the pristine state (black) and with (red) 1 ML LB film deposited on top. Inset: optical image of the ReS_2 device coated with 1 ML LB film. The dotted lines in (c) and (d) mark T_1 and T_2 during heating. The dashed lines separate the heating and cooling regimes. e) Schematic illustration of a two-stage mechanism for P-NW formation facilitated by interfacial ReS_2 . a-P: amorphous polymer chain. c-P: crystalline polymer chain.

an E_c below 0.02 V nm^{-1} . To assess the magnitude of polarization in the P-NWs, we monitored the in situ conductance change in 1L ReS_2 due to ferroelectric polarization doping of P(VDF-TrFE) during the P-NW formation process. As shown in Figure 5c, for a sample deposited with 9 ML of LB film, the conductance S of ReS_2 exhibits a sharp increase between T_1 and T_2 , which is more than one order of magnitude higher than the thermal effect induced conductance variation in this ReS_2 sample before being coated with P(VDF-TrFE). This effect clearly illustrates the significant enhancement of polarization in the crystalline P-NWs compared with the polycrystalline LB film, as one would expect a lower polarization doping from the unstructured LB film with increasing temperature due to the pyroelectric effect. An even larger change is observed in the sample coated with 1 ML P(VDF-TrFE) (Figure 5d). The channel conduction is increased by over 10^3 -fold between T_1 and T_2 , which is more than two orders of magnitude higher than the change for ReS_2 in the pristine state. Upon cooling, the pristine ReS_2 samples recover the conductance S to the initial levels, as expected for a thermally activated behavior. For samples deposited with P(VDF-TrFE), in contrast, S only decreases moderately upon cooling, confirming that the P-NW film is stable. The fact that the conduction change in the ReS_2 sample deposited with 1 ML P(VDF-TrFE) is more than 10^2 times higher than the 9 ML sample demonstrates that the fine NWs not only preserve ferroelectricity, but likely possess even higher crystalline order with enhanced out-of-plane polar alignment, which is consistent with the lower E_c compared with the wide NWs.

The AFM and electrical characterizations reveal a two-stage P-NW formation process. The initial LB film is polymorphous, possessing both small crystallites and amorphous region (Figure 5e). As the sample is heated to T_1 (stage I), textures of short, fine P-NWs start to emerge, which are initially randomly oriented. The polymer chain is perpendicular to the NW orientation (Figure 2f). At the second transition temperature T_2 (stage II), the NWs gain sufficient thermal energy and become mobile on ReS_2 . The interfacial interaction promotes the realignment of the NWs, with the adjacent NWs merging into longer fine ($\approx 10 \text{ nm}$ width) or wide ($\approx 35 \text{ nm}$ width) NWs. The merged NWs are mostly aligned along the direction perpendicular to b_R -axis of ReS_2 . For the LB films thinner than 6 ML, the fine and wide P-NWs coexist to ensure a full surface

coverage of P-NWs on ReS_2 . For the 6 and 9 ML LB films, all fine NWs coalesce into wide NWs, resulting into close-packed uniform films, suggesting that the wide NW structure is more favorable when sufficient volume of the starting material is available.

Despite the starting LB film thickness, the final form of the P-NWs possesses similar width/height (Figure 4b), suggesting a self-termination process. This is similar to the thermal annealing effect on P(VDF-TrFE) LB films prepared on doped Si substrates below 4 ML thickness, where the initially uniform films segregate into isolated nanomesa structures with uniform heights of 9–10 nm.^[31] Increasing the layer number only increases the density of the nanomesas, till they merge into a continuous film, without changing its height. The nanomesa formation process has been explained by considering the surface and elastic energies of the nanostructure and its interfacial interaction with the substrate.^[32,33] These three energy contributions compete with each other: the surface and elastic energies prefer a uniform film distribution to maximize the surface to volume ratio, while the interaction between P(VDF-TrFE) and the substrate is repulsive in nature, driving the pattern coarsening to reduce the interface area. The net energy can be minimized at a critical structure height h_c regardless of the lateral dimension of the nanomesa. Similar scenario can be adopted to explain the P-NW formation on ReS_2 . The key difference between the nanomesa structure and our system is the existence of an epitaxial relationship between P(VDF-TrFE) and ReS_2 , which also lowers the interface energy. As shown in Figure 2g, the interfacial bonding density along the P-NW direction (y -axis) is much lower than the one along the b_R direction (x -axis). The epitaxial bonding energy prefers to have the polymer chain aligned along the b_R direction (x -axis), with the corresponding NW orientation perpendicular to b_R , while the repulsive interfacial interaction leads to a corrugated surface that is stabilized at certain NW widths to optimize the contact area. In the direction perpendicular to Re-chain direction (y -axis), the surface/elastic energy dominates due to the low interfacial bonding density, leading to continuous long wires with large surface area. The net morphology is thus a result of the energy competition between the interfacial synergy and the self-energy of P(VDF-TrFE).

3. Conclusion

Unlike the polycrystalline or polymorphous P(VDF-TrFE) films, the close-packed P-NW films possess high crystallinity due to the interfacial epitaxial relation, enhanced out-of-plane polar alignment, and reduced coercive voltages that can be as low as 0.1 V, making them highly competitive for energy-efficient device applications. The large out-of-polarization of P-NW gate enables a remarkable nonvolatile current switching ratio of exceeding 10^8 in bilayer ReS_2 , which is among the highest values reported on P(VDF-TrFE)-gated 2D FETs.^[6,7] As our approach is easily scalable for wafer-size production, it lays the important groundwork for implementing the ferroelectric polymer/2D vdW heterostructure for light-weight, low-power, wearable nanoelectronics and optoelectronics.

4. Experimental Section

Sample Preparation: Selected n -layer ($n\text{L}$, $n = 1\text{--}10$) ReS_2 flakes were mechanically exfoliated from bulk single crystals on elastomeric films (Gel-Film WF $\times$ 4 1.5 mil from Gel-Pak) and transferred on SiO_2 (290 nm)/Si substrates using an all-dry transfer technique. The layer thickness was identified via the frequency difference Δ between the Mode I and Mode III in the Raman spectra (Figure S1, Supporting Information).^[34]

P(VDF-TrFE) (70:30 mol%) copolymer films were deposited on $\text{ReS}_2/\text{SiO}_2$ or ReS_2 single crystals by the horizontal LB technique from a water subphase. The P(VDF-TrFE) thin film was deposited one ML at a time. The thickness of 1 ML LB film is ≈ 2.0 nm. The as-grown P(VDF-TrFE) film is polycrystalline with low fraction of amorphous phase, with smooth morphology and no visible pinholes.^[2] The samples were then annealed at 135 °C for 80 min to obtain the highly ordered P-NW films. The copolymer composition ratio of 70/30 VDF/TrFE was chosen because of its relatively high remnant polarization ($\approx 10 \mu\text{C cm}^{-2}$).^[35,36]

TEM Studies: The TEM measurements were performed using a 200 kV TEM system (Tecnai Osiris Scanning, FEI) equipped with a field emission gun. The P-NW films are stable under this energy electron beam. The cross-sectioned TEM samples were prepared using the standard focused ion beam (FIB) lift-off technique via a FIB-SEM system (Thermo

Science Helios NanoLab 660, FEI). A 5 nm thick Pt/Pd film was sputter-coated on top of the sample to prevent charge buildup during sample preparation. A 2 μm thick layer of Pt was then deposited to protect the sample during the ion milling. The cross-sectioned sample was mounted on a TEM copper grid and was further thinned to electron transparency.

Raman Characterization: Raman measurements were carried out using a micro-Raman system (Renishaw InVia plus, Renishaw). Raman spectra were collected with a 514.5 nm laser in reflection mode through a 50 $\times$ objective lens with an accumulation time of 10 s. To avoid heating damage, the laser power was below 1 mW. For the polarized Raman measurements, the incident laser polarization was fixed with a linear polarizer, and the Raman signal was measured parallel to the laser polarization using a linear analyzer. The parallel polarization Raman signal was collected by rotating the sample from angle $\varphi = 0^\circ$ – 360° in 10° steps.

Temperature-Dependent in situ AFM Studies: The AFM and PFM measurements were conducted in a Bruker Multimode 8 AFM system. For the in situ thermal annealing measurements, the sample was placed on the AFM sample holder of the heating/cooling module. The temperature was controlled by the Bruker TAC Thermal Application Controller system. The sample was slowly heated to progressively higher temperatures. Before imaging, the sample was held for 10 min at the target temperature after the temperature was stabilized. The in situ topography scanning was conducted in tapping mode with silicon nitride AFM probes (Bruker SCANASYST-AIR, spring constant k of 0.2–0.8 N m $^{-1}$, resonant frequency f_0 of 45–95 kHz). Due to thermal drift, the same area was not tracked. This will not affect the analysis since the sample is uniform on the large scale.

PFM Studies: The vertical PFM measurements were performed in contact mode with conductive PtIr-coated AFM probes (Bruker SCMPIC-V2, spring constant k of 0.03–0.2 N m $^{-1}$, resonant frequency f_0 of 4–10 kHz). The lateral PFM (L-PFM) measurements were performed with conductive PtIr-coated AFM probes (NanoSensors PPP-EFM, spring constant k of 0.5–9.5 N m $^{-1}$, resonant frequency f_0 of 45–115 kHz). The scanning direction was perpendicular to the cantilever axis. The scanning-angle-dependent L-PFM signal was collected by rotating the sample from 0° to

180° in 15° steps. The noise floor for L-PFM is calibrated using the uniformly polarized domain and domain wall written on high quality epitaxial (001) $\text{PbZr}_{0.2}\text{Ti}_{0.8}\text{O}_3$ thin films (Figure S6, Supporting Information).^[37]

FET Device Fabrication and Characterization: Cr/Au (5/25nm) electrodes were pre-patterned on SiO_2 (290nm)/Si substrates in the two-point geometry using photolithography. Selected ReS_2 flakes were transferred on the electrodes, forming FET devices. P(VDF-TrFE) thin films were then deposited on the ReS_2 devices by the horizontal LB deposition technique. All electrical measurements were carried out using semiconductor parameter analyzer (Keysight 1500A) in ambient conditions.

* * * * *

Supporting Information follows the References.

Acknowledgments The authors thank Xi Huang and Michael Bengston for technical assistance, and Yongfeng Lu for the access to the Raman system. This work was primarily supported by the U.S. Department of Energy (DOE), Office of Science, Basic Energy Sciences (BES), under Award No. DE-SC0016153 (sample preparation and characterization, FET device fabrication and characterization). S.S. and S.D. acknowledge the support of the Nebraska Center for Energy Research. Z.A. and J.S. acknowledge the support of the National Science Foundation (NSF) through the Materials Research Science and Engineering Center (MRSEC) (Grant No. DMR-1420645). The research was performed in part in the Nebraska Nanoscale Facility: National Nanotechnology Coordinated Infrastructure under the NSF Award No. ECCS: 2025298, and with support from the Nebraska Research Initiative through the Nebraska Center for Materials and Nanoscience and the Nanoengineering Research Core Facility at the University of Nebraska-Lincoln.

Conflict of Interest The authors declare no conflict of interest.

Author Contributions D.L. and S.S. contributed equally to this work. X.H. and D.L. conceived the project and designed the experiments. X.H. supervised the project. D.L. prepared the ReS_2 samples and devices, and carried out Raman and AFM characterizations. S.S. and S.D. prepared the P(VDF-TrFE) LB films. Z.A. and J.S. performed the TEM studies. D.L. and K.W. carried out the PFM studies. D.L. and S.S. prepared the P-NW films and carried out the electrical measurements. D.L. and X.H. wrote the manuscript. All authors discussed the results and contributed to the manuscript preparation.

Data Availability The data that support the findings of this study are available from the corresponding author upon reasonable request.

References

- [1] A. V. Bune, V. M. Fridkin, S. Ducharme, L. M. Blinov, S. P. Palto, A. V. Sorokin, S. G. Yudin, A. Zlatkin, *Nature* 1998, **391**, 874.
- [2] S. Ducharme, S. Palto, V. M. Fridkin, in *Handbook of Thin Films*, Vol. 3, (Ed: H. Singh Nalwa), Academic Press, Burlington, MA, USA 2002, p. 545.
- [3] Z. Hu, M. Tian, B. Nysten, A. M. Jonas, *Nat. Mater.* 2009, **8**, 62.
- [4] Y. Yuan, T. J. Reece, P. Sharma, S. Poddar, S. Ducharme, A. Gruverman, Y. Yang, J. Huang, *Nat. Mater.* 2011, **10**, 296.
- [5] M. Li, H. J. Wondergem, M.-J. Spijkman, K. Asadi, I. Katsouras, P. W. Blom, D. M. De Leeuw, *Nat. Mater.* 2013, **12**, 433.
- [6] X. Hong, *J. Phys.: Condens. Matter* 2016, **28**, 103003.
- [7] H. Ryu, K. Xu, D. Li, X. Hong, W. Zhu, *Appl. Phys. Lett.* 2020, **117**, 080503.
- [8] Y. T. Lee, H. Kwon, J. S. Kim, H.-H. Kim, Y. J. Lee, J. A. Lim, Y.-W. Song, Y. Yi, W.-K. Choi, D. K. Hwang, *ACS Nano* 2015, **9**, 10394.
- [9] K. L. Kim, W. Lee, S. K. Hwang, S. H. Joo, S. M. Cho, G. Song, S. H. Cho, B. Jeong, I. Hwang, J.-H. Ahn, *Nano Lett.* 2016, **16**, 334.
- [10] Z. Xiao, J. Song, D. K. Ferry, S. Ducharme, X. Hong, *Phys. Rev. Lett.* 2017, **118**, 236801.
- [11] D. Li, Z. Xiao, S. Mu, F. Wang, Y. Liu, J. Song, X. Huang, L. Jiang, J. Xiao, L. Liu, S. Ducharme, B. Cui, X. Hong, L. Jiang, J.-F. Silvain, Y. Lu, *Nano Lett.* 2018, **18**, 2021.
- [12] X. Wang, Y. Chen, G. Wu, D. Li, L. Tu, S. Sun, H. Shen, T. Lin, Y. Xiao, M. Tang, W. Hu, L. Liao, P. Zhou, J. Sun, X. Meng, J. Chu, J. Wang, *npj 2D Mater. Appl.* 2017, **1**, 38.
- [13] X. Liu, R. Liang, G. Gao, C. Pan, C. Jiang, Q. Xu, J. Luo, X. Zou, Z. Yang, L. Liao, *Adv. Mater.* 2018, **30**, 1800932.
- [14] Y. Chen, Y. Zhou, F. Zhuge, B. Tian, M. Yan, Y. Li, Y. He, X. S. Miao, *npj 2D Mater. Appl.* 2019, **3**, 31.
- [15] L. Lv, F. Zhuge, F. Xie, X. Xiong, Q. Zhang, N. Zhang, Y. Huang, T. Zhai, *Nat. Commun.* 2019, **10**, 3331.
- [16] G. Wu, B. Tian, L. Liu, W. Lv, S. Wu, X. Wang, Y. Chen, J. Li, Z. Wang, S. Wu, H. Shen, T. Lin, P. Zhou, Q. Liu, C. Duan, S. Zhang, X. Meng, S. Wu, W. Hu, X. Wang, J. Chu, J. Wang, *Nat. Electron.* 2020, **3**, 43.
- [17] M. Benz, W. B. Euler, O. J. Gregory, *Macromolecules* 2002, **35**, 2682.
- [18] J. Andrew, D. Clarke, *Langmuir* 2008, **24**, 670.
- [19] S.-H. Park, H. B. Lee, S. M. Yeon, J. Park, N. K. Lee, *ACS Appl. Mater. Interfaces* 2016, **8**, 24773.
- [20] T. Fukuma, K. Kobayashi, T. Horiuchi, H. Yamada, K. Matsushige, *Jpn. J. Appl. Phys.* 2000, **39**, 3830.
- [21] P. Sharma, T. Reece, D. Wu, V. M. Fridkin, S. Ducharme, A. Gruverman, *J. Phys.: Condens. Matter* 2009, **21**, 485902.
- [22] E. Bellet-Amalric, J. Legrand, *Eur. Phys. J. B* 1998, **3**, 225.

- [23] J. Song, H. Lu, S. Li, L. Tan, A. Gruverman, S. Ducharme, *Nanotechnology* 2016, 27, 015302.
- [24] Y.-Y. Choi, P. Sharma, C. Phatak, D. J. Gosztola, Y. Liu, J. Lee, B. Lee, J. Li, A. Gruverman, S. Ducharme, S. Hong, *ACS Nano* 2015, 9, 1809.
- [25] Z. Xiao, S. Poddar, S. Ducharme, X. Hong, *Appl. Phys. Lett.* 2013, 103, 112903.
- [26] S. Ducharme, V. M. Fridkin, A. V. Bune, S. Palto, L. Blinov, N. Petukhova, S. Yudin, *Phys. Rev. Lett.* 2000, 84, 175.
- [27] X. Chen, X. Zhang, M. A. Koten, H. Chen, Z. Xiao, L. Zhang, J. E. Shield, P. A. Dowben, X. Hong, *Adv. Mater.* 2017, 29, 1701385.
- [28] H. Ohigashi, K. Omote, T. Gomyo, *Appl. Phys. Lett.* 1995, 66, 3281.
- [29] L. Blinov, V. Fridkin, S. Palto, A. Sorokin, S. Yudin, *Thin Solid Films* 1996, 284, 474.
- [30] P. Sharma, D. Wu, S. Poddar, T. J. Reece, S. Ducharme, A. Gruverman, *J. Appl. Phys.* 2011, 110, 052010.
- [31] M. Bai, S. Ducharme, *Appl. Phys. Lett.* 2004, 85, 3528.
- [32] J. Li, Y. Luo, M. Bai, S. Ducharme, *Appl. Phys. Lett.* 2005, 87, 213116.
- [33] J. Li, Y. Luo, M. Bai, S. Ducharme, *J. Mech. Phys. Solids* 2006, 54, 2162.
- [34] D. A. Chenet, O. B. Aslan, P. Y. Huang, C. Fan, A. M. van der Zande, T. F. Heinz, J. C. Hone, *Nano Lett.* 2015, 15, 5667.
- [35] T. Furukawa, *Phase Transitions: Multinatl. J.* 1989, 18, 143.
- [36] S. M. Nakhmanson, M. B. Nardelli, J. Bernholc, *Phys. Rev. Lett.* 2004, 92, 115504.
- [37] D. Li, X. Huang, Z. Xiao, H. Chen, L. Zhang, Y. Hao, J. Song, D.-F. Shao, E. Y. Tsymbal, Y. Lu, X. Hong, *Nat. Comm.* 2020, 11, 1422.

Supporting Information

Assembly of Close-Packed Ferroelectric Polymer Nanowires via Interface-Epitaxy with ReS₂

Dawei Li, Shuo Sun, Kun Wang, Zahra Ahmadi, Jeffrey E. Shield, Stephen Ducharme, and Xia Hong*

Contents

1. Characterizations of ReS₂ and P(VDF-TrFE) Nanostructures
2. Modeling of (110) P(VDF-TrFE) on ReS₂
3. Lateral Piezoresponse Force Microscopy Study of P(VDF-TrFE) Nanowire Films
4. Effect of High Temperature Annealing on P(VDF-TrFE) Films on ReS₂

1. Characterizations of ReS₂ and P(VDF-TrFE) Nanostructures

Figure S1 shows the Raman spectra of mechanically exfoliated n -layer (n L) ReS₂ flakes on SiO₂/Si substrate. The layer thickness can be determined via the frequency difference Δ between the Mode I and Mode III in the Raman spectra.^[1]

Figure S1. Raman characterizations of mechanically exfoliated ReS₂ flakes. a) Raman spectrum of a 1L ReS₂ showing Mode-I at 134.3 cm⁻¹ and Mode-III at 151.8 cm⁻¹. Inset: optical image of the sample. b) Raman spectrum of the 2L ReS₂ device shown in Fig. 3e, with Mode-I at 135.6 cm⁻¹ and Mode-III at 150.4 cm⁻¹. Inset: optical image of the sample. c) Raman spectrum of a 4L ReS₂ with Mode-I at 137.3 cm⁻¹ and Mode-III at 150.8 cm⁻¹.

Figure S2 illustrates how we determined the width of the P(VDF-TrFE) nanowires (P-NWs). As the P-NWs are closely packed (Figure 2b), we counted the number of NWs over a large distance (e.g., Figure 1b) to extract the average width. The error bars were calculated from the results taken on five different locations.

Figure S2. A sub-area of the AFM topography image in Figure 1b showing the morphology of 6 P-NWs, with (lower panel) the height profile along the red dashed line.

Figure S3a-c show the P-NWs formed on 2L to few layer ReS_2 flakes. The controlled formation of P-NWs on ReS_2 can be further extended to thick (Figure S3d) and bulk ReS_2 samples (Figure 2a). For comparison, we prepared P(VDF-TrFE) using identical fabrication methods on five different 2D layered van der Waals (vdW) materials (Figure S4), where we observed randomly distributed rice-like nano-grains, in sharp contrast to the P-NWs formed on ReS_2 . Similar nano-grains have previously been reported for P(VDF-TrFE) spin-coated on graphene after thermal annealing, which show a coercive voltage orders of magnitude higher than the P-NWs on ReS_2 .^[2] Due to the structural similarity of the P(VDF-TrFE) nanostructures, we expect the samples prepared on other vdW materials show similar ferroelectric properties.

Figure S3. P-NW films formed on few-layer and thick flakes of ReS_2 . a) Optical image and b-c) AFM topography images of the P-NW film formed on a ReS_2 flake with different layer thicknesses. d) AFM topography image of the P-NW film formed on a thick ReS_2 flake (about 160 nm thick). Inset: optical image of the sample.

Figure S4. P(VDF-TrFE) nanostructures formed on various 2D vdW materials. AFM topography images of thermally treated 9 monolayer (ML) Langmuir-Blodgett (LB) films prepared on a) 2H-MoS₂, b) graphene, c) $\alpha\text{-In}_2\text{Se}_3$, d) black phosphorus, and e) TiS₃. The crystalline orientations of the 2D vdW base layers are labelled. All scale bars are 200 nm.

2. Modeling of (110) P(VDF-TrFE) on ReS₂

For (110) P(VDF-TrFE), the inter-layer spacing is about 4.5 Å,^[3] which is much larger than that for the P-NWs (2.48 ± 0.01 Å). In Figure S5a, we superimposed the atomic arrangements of (110) P(VDF-TrFE) on the high-resolution transmission electron microscopy (HRTEM) image of the P-NW on ReS₂ shown in Figure 2f, which clearly do not match. We thus ruled out the possibility of (110) orientation for the P-NWs. This is consistent with the fact that there is no obvious epitaxial lattice relation between (110) P(VDF-TrFE) and ReS₂ in the *y*-*z* plane (Figure S5b).

Figure S5. Modeling of (110) P(VDF-TrFE) on ReS₂. a) HRTEM image of the P-NW on ReS₂ (Figure 2f in the main text) superimposed with the atomic arrangements of (110) P(VDF-TrFE). b) Schematic side views of (110) P(VDF-TrFE) on ReS₂. The dashed lines mark the unit cells for P(VDF-TrFE) and ReS₂. The laboratory coordinate system and crystalline orientations of P(VDF-TrFE) and ReS₂ are labelled.

3. Lateral Piezoresponse Force Microscopy Study of P(VDF-TrFE) Nanowire Films

We performed lateral piezoresponse force microscopy (L-PFM) studies to probe the in-plane polarization of the P-NW film. Figures 6a-b show the L-PFM images taken on the same domain structure shown in Figures 3b-c, which reveal consistently low signal for the as-grown, P_{up} , and P_{down} domain regions. To calibrate the noise level, we also performed L-PFM imaging on a uniformly polarized P_{up} domain on a (001) orientated epitaxial PZT thin film, which does not possess lateral polarization. The L-PFM amplitude signal taken on the P-NW film is close to the calibrated noise level, and does not show apparent dependence on the scanning angle (Figure S6c).

For comparison, we also showed the polar plot of L-PFM amplitude signal taken on a $\text{PbZr}_{0.2}\text{Ti}_{0.8}\text{O}_3$ (PZT) domain wall (DW), where the chiral rotation of surface dipoles leads to an in-plane polarization perpendicular to the DW direction.^[4] Strong L-PFM signal was observed for the scanning direction perpendicular to the DW (parallel to the in-plane polarization). These results confirm a lack of in-plane component of polarization in P-NW film, which crystallizes in the (010) orientation.

Figure S6. L-PFM characterization of P-NW film. a) L-PFM phase and b) amplitude images of the domain structure shown in Figures 3b-c in the main text. The signal profiles along the dashed lines are shown in the lower panels in Figures 3b-c. c, Polar plot of L-PFM amplitude signal vs. scanning angle. Also shown are the data taken on the P_{up} domain and domain wall of an epitaxial (001) PZT film grown on 10 nm $\text{La}_{0.67}\text{Sr}_{0.33}\text{MnO}_3$ buffered (001) SrTiO_3 substrate. All data in (c) are normalized with respect to the L-PFM amplitude signal for the (001) PZT P_{up} domain.

5. Effect of High Temperature Annealing on P(VDF-TrFE) Films on ReS_2

The NW formation process is very sensitive to the thermal annealing temperature. Figure S7 shows a series of *in situ* AFM images taken on a 1 ML P(VDF-TrFE) LB film prepared on ReS_2 during the heating and cooling processes. When the sample was heated to 130 °C, the film reconstructs into well aligned NWs. When the sample was further heated above 140 °C, the P-NWs quickly melt, and form a threaded-beads-structure before breaking into isolated droplets. Interestingly, highly ordered NWs re-emerge from the droplets during the cooling process below 140 °C, indicating the effect of strong interface epitaxy interaction between P(VDF-TrFE) and ReS_2 .

Figure S7. Effect of high temperature thermal annealing. *In situ* AFM images taken on a 1 ML P(VDF-TrFE) LB film prepared on ReS₂, showing the P-NW formation, melting, and re-emerging processes.

References

- [1] D. A. Chenet, O. B. Aslan, P. Y. Huang, C. Fan, A. M. van der Zande, T. F. Heinz, J. C. Hone, *Nano letters* 2015, 15, 5667.
- [2] K. L. Kim, W. Lee, S. K. Hwang, S. H. Joo, S. M. Cho, G. Song, S. H. Cho, B. Jeong, I. Hwang, J.-H. Ahn, Y.-J. Yu, T. J. Shin, S. K. Kwak, S. J. Kang, C. Park, *Nano Letters* 2016, 16, 334.
- [3] S. Ducharme, S. Palto, V. M. Fridkin, in *Handbook of Thin Films*, Elsevier, 2002, 545.
- [4] D. Li, X. Huang, Z. Xiao, H. Chen, L. Zhang, Y. Hao, J. Song, D.-F. Shao, E. Y. Tsymbal, Y. Lu, *Nature communications* 2020, 11, 1.