

1981

Influence of Age, Sex, and Calcium and Phosphorus Levels on the Mechanical Properties of Various Bones in Swine

T. D. Crenshaw

University of Wisconsin

E. R. Peo, Jr.

University of Nebraska-Lincoln

A. J. Lewis

University of Nebraska-Lincoln, alewis2@unl.edu

B. D. Moser

University of Nebraska-Lincoln

D. Olson

Iowa State University

Follow this and additional works at: <http://digitalcommons.unl.edu/animalscifacpub>



Part of the [Animal Sciences Commons](#)

Crenshaw, T. D.; Peo, Jr., E. R.; Lewis, A. J.; Moser, B. D.; and Olson, D., "Influence of Age, Sex, and Calcium and Phosphorus Levels on the Mechanical Properties of Various Bones in Swine" (1981). *Faculty Papers and Publications in Animal Science*. 658.

<http://digitalcommons.unl.edu/animalscifacpub/658>

This Article is brought to you for free and open access by the Animal Science Department at DigitalCommons@University of Nebraska - Lincoln. It has been accepted for inclusion in Faculty Papers and Publications in Animal Science by an authorized administrator of DigitalCommons@University of Nebraska - Lincoln.

INFLUENCE OF AGE, SEX AND CALCIUM AND PHOSPHORUS LEVELS ON THE MECHANICAL PROPERTIES OF VARIOUS BONES IN SWINE^{1,2}

T. D. Crenshaw³, E. R. Peo, Jr., A. J. Lewis, B. D. Moser and D. Olson⁴

University of Nebraska, Lincoln 68583

Summary

Seventy-two 4-week-old pigs were randomly assigned by sex (gilts, barrows, boars) to two dietary treatments and four age periods for determinations of the effects of age, sex and Ca and P levels on the mechanical properties of various bones in swine. Pigs were individually fed diets containing either .4, .4% Ca,P (T1) or .8, .8% Ca,P (T2). Slaughter times (age period) were approximately 1 (A1), 3 (A3), 5 (A5) and 7 (A7) months after the initiation of the trial. The femur (Fem), humerus (Hum), third and fourth metacarpal (3MC, 4MC), third and fourth metatarsal (3MT, 4MT), third rib (Rib) and thoracic vertebrae were collected at each age period for mechanical tests and determination of percentage of ash. Bending moment, ultimate stress, yield stress and modulus of elasticity were determined by a flexure test in which the bone was treated as a simply supported, centrally-loaded beam (three-point loading). Bending moment of bones from boars was similar to that of bones from gilts or barrows. When expressed as force per unit area, the ultimate stress of bones from boars was less than that of bones from gilts or barrows. Percentage of ash did not differ significantly between sexes, but tended to be lower in bones from boars than in bones from gilts or barrows. Bones from pigs fed T2 had a higher bending moment than bones from pigs fed T1, regardless of age. At A1, the Fem, Hum and Rib of pigs

fed T2 were able to withstand a greater stress than the same bones of pigs fed T1. At A3 and A5, the ultimate stress of all bones increased with increasing levels of dietary Ca,P. At A7, the Fem, 4MT and Rib failed to show a response to increased levels of Ca,P.

(Key Words: Bone, Sex, Age, Calcium, Phosphorus, Swine.)

Introduction

The physical characteristic, strength, has been used by nutritionists to assess mineralization of bones. Burnett (1908) used bone strength to demonstrate the value of P in feedstuffs for swine. More recently, Hayes *et al.* (1979) concluded that bone strength was the best trait from which to estimate the bioavailability of dietary P.

The ideal bone(s) for assessing mineralization in swine may vary with age, sex and possibly other biological as well as economical factors. For example, bones from the front or hind feet are more accessible and economically more appealing for testing than is the femur or humerus. Tanksley (1979) implied that the femur is a better indicator of bone development than are metacarpal bones, and that Ca and P requirements for maximum bone development differ widely, depending upon the bone used. Henrikson (1968) demonstrated in dogs that vertebrae and then ribs are depleted of Ca before long bones. Using ⁴⁵Ca, Pond *et al.* (1969) reported similar activity among vertebrae, mandibles, nasal turbinates and the proximal and distal ends of both the femur and humerus of young pigs.

Researchers have recently reported that boars have a Ca-P requirement for maximum bone breaking strength higher than current NRC (1973)-recommended levels of optimum growth (Tanksley *et al.*, 1976; Nimmo *et al.*, 1980). For the most part, NRC-recommended levels for Ca and P have been based on research

¹Published as Paper No. 6094, Journal Ser., Nebraska Agr. Exp. Sta.

²Dept. of Anim. Sci. Acknowledgment is made to Chuck Clanton for assistance with engineering equations and to Cecilia Stodd and Mary Barnes for laboratory assistance.

³Current address: Meat and Anim. Sci. Dept., Univ. of Wisconsin, Madison.

⁴Current address: Anim. Sci. Dept., Iowa State Univ., Ames.

with growing-finishing barrows and gilts. Little work has been done to determine directly the effect of sex on the mechanical properties of bone.

The purpose of the research reported herein was to determine the influences of age, sex and Ca-P levels on the mechanical properties of various bones in swine.

Materials and Methods

Seventy-two 4-week-old crossbred pigs were randomly assigned by sex (gilts, barrows, boars) to two dietary treatments and four age periods. Pigs were individually fed a 16% corn-soybean meal basal diet (table 1) containing either .4, .4% (T-1) or .8, .8% (T-2) Ca and P. Pig weights and feed consumption were measured biweekly. Pigs were housed in an environmentally regulated building with 1.07 m × 1.52 m individual pens and completely slatted concrete floors. The age periods designated for study were 1 (A1), 3 (A3), 5 (A5) and 7 (A7) months after the initiation of the trial, but the pigs were actually slaughtered at 18, 82, 145 and 192 days of age.

At slaughter, eight bones were collected for the determination of mechanical properties and percentage of ash. The bones were all from the right side and consisted of the femur (Fem), humerus (Hum), third and fourth metacarpal (3MC, 4MC), third and fourth metatarsal (3MT, 4MT), third rib (Rib) and the right half of the thoracic vertebra (Ver) located at the third rib. Bones were cleaned of adhering tissue by autoclaving at 116 C and 1.3 kg/cm² pressure. Depending upon the amount of tissue surrounding the bone, the time of autoclaving was adjusted so that blood around the bone itself was still bright red. We considered the bones to be "raw bones" even though they had been exposed for a short time to autoclaving. Before and after cleaning, bones were stored at -28 C in plastic bags to maintain the original moisture content. After mechanical tests and measurements were made, the bones were extracted in anhydrous ethyl-ether for removal of lipid material and then ashed at 600 C.

The mechanical properties of all bones except the vertebrae were determined by a flexure test with an Instron Universal Testing Machine⁵. The flexure test has been widely used for determining the mechanical properties

TABLE 1. COMPOSITION AND ANALYSIS OF DIETS

Ingredient	% Ca,P	
	.4, .4	.8, .8
Corn, yellow (IFN 4-02-935)	76.86	74.30
Soybean meal (IFN 5-04-604)	20.58	21.04
Dicalcium phosphate (IFN 6-01-080)	.60	2.92
Limestone (IFN 6-02-632)	.31	.09
Trace mineral mix ^a	.10	.10
Selenium premix ^a	.05	.05
Salt, iodized (IFN 6-04-151)	.50	.50
Vitamin premix ^b	1.0	1.0
	100.00	100.00
Chemical analysis:		
Dry matter, %	87.8	87.9
Protein, %	15.6	15.4
Ca, %	.41	.82
P, %	.44	.86

^aContributed the following in milligrams/kilogram of diet: Zn, 200; Fe, 100; Mn, 55; Cu, 10; Co, 1.0; I, 1.5; sodium selenite, .1.

^bContributed the following per kilogram of diet: vitamin A, 3,300 IU; vitamin D₃, 440 IU; riboflavin, 2.2 mg; d-pantothenic acid, 13.2 mg; niacin, 17.6 mg; choline chloride, 110 mg; vitamin B₁₂, .022 mg; ethoxyquin, 4.4 mg; menadione sodium bisulfate, 2.2 mg; vitamin E, 22 IU.

of bones (Baker and Haugh, 1979). The bone was treated as a beam supported at each end and a force was applied at midshaft. Force was applied at a constant rate (5 mm/min) to all bones, and a recorder was used to plot the force-deflection curve (figure 1), where chart movement was proportional to crosshead movement. The test was stopped when the curve leveled off or reached a peak or maximum force, and the ultimate stress of the bone was determined. Although most bones did not break apart at this point, if further deformation of bending occurred, the bone failed to withstand any greater increase in force, as indicated by the dashed line portion of the curve beyond point A (figure 1).

In the initial phase of the curve, force increased in a linear fashion and was proportional to deformation. It is during this phase that elastic deformation occurs (Evans, 1973), and up

⁵Model 1123, Instron Corp., Canton, MA 02021.




Figure 1. Typical force-deformation curve recorded in mechanical test of bone. A = peak force, kilograms. B = inflection force, kilograms. C = deformation to inflection point, millimeters. D = deformation to peak point, millimeters.

to the inflection point no permanent damage is done to the bone. At the inflection point, maximum yield stress can be determined. Beyond the inflection point, permanent damage is done to the bone, or plastic deformation is exhibited.

Measurements were made at the point of loading (midshaft) to determine outside and inside diameters of the bones. Impressions were made of the cross sections of a representative portion of each bone, and the moment of inertia was calculated according to the method of Granik and Stein (1973). Diameters of the cross sections were used in equations for calculating the moment of inertia of known shapes, and the equation with the lowest percentage error was then used for that bone (figure 2). By this method, we determined that the equation for the moment of inertia of an ellipse more closely fits the shape of the femur and humerus, while the equation for an elliptical quadrant more closely fits the metacarpal, metatarsal and rib.

Equations used for calculating the various strength parameters involving elliptical cross sections have been reported by Weir *et al.* (1949). Equations used for bones with a cross section of an elliptical quadrant were taken from an engineering handbook by Griffel (1966).




Figure 2. Determination of equations used for calculating the moment of inertia of various bone cross sections. The number in parentheses is the percentage difference from I^b . I^b = the area moment of inertia about the neutral axis determined by procedure used by Granik and Stein (1973). I^c = moment of inertia determined with the equation for an ellipse. B and b are outside and inside diameters perpendicular to the direction of force, while D and d are diameters parallel to the direction of applied force. The arrow indicates the direction of applied force. I^d = moment of inertia determined with the equation for an elliptical quadrant with the diameters determined as above.

Bending moment is simply an adjustment of the force applied to the bone to account for differences in the span over which the force is applied. It is determined by the formula,

$$\text{Bending moment (kilograms-centimeters)} = \frac{\text{force} \times \text{length}}{4}$$

where length equals the distance between the two fulcrum points that support the bone. Bending moment allows comparisons of force to be made between bones of different lengths.

Stress is force per unit area. The area moment of inertia accounts not only for differences in

area, but also for differences in shape of the bone cross section through which the force is applied (table 2). Stress is calculated as follows:

Stress (kilograms/square centimeter) =

$$\frac{\text{force} \times \text{length} \times C}{4 \times \text{moment of inertia}}$$

where C equals the distance from the neutral axis to the extreme fiber. For an ellipse, C equals one-half the diameter that is parallel to the force applied. For an elliptical quadrant, C equals the diameter minus four times the diameter divided by 3π . Stress allows comparisons to be made between strengths of bones that differ in length, size and shape.

Strain takes into account the amount of bending or deformation that occurs in the bone as it is being tested. The formula by which it is determined is

$$\text{Strain} = \frac{12 \times \text{deformation} \times C}{\text{length}^2}$$

Strain is unitless, as it is the change in length per unit length.

Modulus of elasticity is the force per unit area (stress) per unit of bending (strain), or more simply the stress:strain ratio:

$$\text{Mod. elas.} = \frac{\text{Force} \times \text{length}^3}{48 \times \text{moment inertia} \times \text{deformation}}$$

Modulus of elasticity is a measure of the ability of a bone to return to its original shape and is an indicator of the stiffness or rigidity of the bone.

Each parameter was calculated at both the inflection point or peak by substituting either the inflection force or peak force and the deformation at either the peak or inflection point.

The vertebrae were tested by a method similar to a hardness test (Evans, 1973). A section was cut from the right half of each vertebra so that the bone fitted a v-shaped base when tested. Tests were made midventrally on the vertebra body. A small probe 1.8 mm in diam-

TABLE 2. GAIN AND FEED CONVERSION OF PIGS AS INFLUENCED BY AGE, SEX AND CALCIUM-PHOSPHORUS LEVELS^a

Age	Measure	No. of animals	% Ca,P					
			.4, .4			.8, .8		
			Gilts	Barrows	Boars	Gilts	Barrows	Boars
A1		72						
	ADG, kg		.25	.28	.31	.29	.27	.31
	ADFI, kg		.59	.66	.67	.72	.64	.69
	F/G		2.64	2.96	2.30	2.60	2.48	2.34
A3		54						
	ADG, kg		.61	.60	.64	.63	.63	.65
	ADFI, kg		1.41	1.38	1.46	1.45	1.49	1.46
	F/G ^c		2.31	2.33	2.28	2.33	2.36	2.23
A5		36						
	ADG, kg ^{bb}		.66	.73	.78	.69	.70	.77
	ADFI, kg ^{bb}		1.81	2.02	2.03	2.00	2.12	2.03
	F/G ^{ccd}		2.76	2.78	2.61	2.89	3.02	2.64
A7		18						
	ADG, kg ^{bbcc}		.61	.68	.79	.64	.68	.80
	ADFI, kg ^{bbd}		2.02	2.27	2.38	2.28	2.48	2.50
	F/G ^{bccd}		3.33	3.36	3.01	3.58	3.65	3.13

^aAdjusted for differences in initial weight. Average initial weight, 9 kilograms.

^bGilts different (P<.05) from barrows and boars.

^{bb}Gilts different (P<.01) from barrows and boars.

^cBarrows different (P<.05) from boars.

^{cc}Barrows different (P<.01) from boars.

^dCa,P level effect (P<.01).

TABLE 3. INFLUENCE OF CALCIUM-PHOSPHORUS LEVELS AND AGE ON VARIOUS BONE CHARACTERISTICS^a

Characteristic	% Ca,P				.4, .4				.8, .8			
	1	3	5	7	1	3	5	7	1	3	5	7
Bending moment, kg bdefgh	31	107	210	279	41	172	316	356				
Ult. stress, kg/cm ² bdegh	446	281	332	454	459	452	558	530				
Yield stress, kg/cm ² bdfg	211	139	148	207	236	234	225	239				
Strain cd²efghi	.055	.050	.059	.061	.064	.050	.046	.060				
Mod. elast., kg/cm ² bdefg	5,141	4,915	5,595	7,684	5,680	7,165	10,145	9,166				
% ash bd²efg	51.0	54.7	56.8	60.3	53.5	58.5	61.1	62.0				
Mom. inertia, cm ⁴ efgi	.047	.285	.570	.705	.056	.319	.578	.785				
Wall thickness, cm bd²fg	.134	.245	.287	.299	.155	.277	.330	.331				

^aPooled across sex and bone.

^bCa,P level effect (P<.01).

^cCa,P level X sex interaction (P<.01).

^dAge effect (P<.01).

^eCa,P level X age interaction (P<.01).

^fCa,P level X bone interaction (P<.01).

^gAge X bone interaction (P<.01).

^hCa,P level X age X bone interaction (P<.01).

ⁱAge X sex interaction (P<.05).

eter was used to ensure total contact with surface of the bone. Rate of deformation was the same as that used for other bones (5 mm/min), and the force required to puncture the bone was measured. Thickness of the cortical bone at the puncture site was measured and used for calculating maximum shear stress in the following equation:

Shear stress (kilograms/square centimeter) =

$$\frac{\text{force}}{\pi d h},$$

where $\pi d h$ is the area of a spherical segment with d the diameter of the probe and h the thickness of the cortical bone. Shear stress is force per unit area. Percentage of ash was determined as for the other bones on the section of vertebra tested.

Statistical analyses were conducted by split-plot analysis (Steel and Torrie, 1960); animals fed the various Ca-P levels, sex and age were the main plots and bones the subplot units. Covariable analyses were used to test the homogeneity of slopes between various parameters as affected by main plot units (Barr *et al.*, 1976).

Results and Discussion

Growth Performance. Growth and feed efficiency responses of pigs are shown in table 2 by

age, sex and Ca, P level. At A1, there were no differences in growth rate or feed efficiency due to sex. At A3, there were no differences in growth rate due to sex, but boars were more efficient ($P < .05$) than barrows or gilts. Boars and barrows gained at a faster rate ($P < .01$) than gilts at A5; the boars were more efficient ($P < .01$) in feed conversion than the barrows and the gilts. At A7, boars gained faster and more efficiently than barrows ($P < .01$), and barrows gained faster ($P < .01$) and more efficiently ($P < .05$) than gilts.

Ca, P level did not affect growth rate at any age period. However, at A5 and A7, pigs fed T1 were more efficient ($P < .01$) than those fed T2. One pig assigned to A5 and fed T1 was slaughtered early because of a spontaneous fracture of its right femur. Two other pigs fed T1 and assigned to A5 broke bones during shipment to slaughter. Bones were collected from these three animals, but it was sometimes necessary to use a bone from the left side rather than the right side.

Bone Properties. The results of the mechanical tests on all bones except the vertebrae, along with their ash content and some geometrical measurements, are shown in tables 3, 4 and 5. The data have been pooled to indicate the main effects, although significant interactions did occur as noted in the footnotes. Subsequent discussion and figures will deal with these interactions. Mechanical tests used to

TABLE 4. INFLUENCE CALCIUM-PHOSPHORUS LEVELS AND SEX ON VARIOUS BONE CHARACTERISTICS^a

Characteristic	.4, .4%			.8, .8%		
	Gilts	Barrows	Boars	Gilts	Barrows	Boars
Bending moment, kg/cm ^f	165	148	157	230	214	220
Ult. stress, kg/cm ² ^{bf}	428	366	340	545	501	454
Yield stress, kg/cm ² ^{bf}	196	178	154	256	233	211
Strain ^{bcd}	.054	.058	.057	.054	.051	.059
Mod. elast., kg/cm ² ^{bf}	6,401	5,648	5,453	8,511	8,147	7,460
% ash	56.0	55.8	55.3	59.0	59.0	58.3
Mom. inertia, cm ⁴ ^{bce}	.348	.394	.463	.377	.424	.503
Wall thickness, cm	.240	.241	.244	.265	.267	.287

^aPooled across age and bone.

^bSex effect ($P < .01$).

^cSex \times age interaction ($P < .01$).

^dSex \times Ca,P level interaction ($P < .01$).

^eSex \times bone interaction ($P < .01$).

^fCa,P level effect ($P < .01$).

TABLE 5. INFLUENCE OF CALCIUM-PHOSPHORUS LEVEL ON VARIOUS BONES

Characteristic	% Ca,P	Bones							4MT	Rib
		Fem	Hum	3MC	4MC	3MT	4MT	Rib		
Bending mom., kg ² bcefh ⁱ	.4, .4	378	471	70	58	53	50	16		
	.8, .8	562	617	107	86	80	76	23		
Ult. stress, kg/cm ² bcefh ⁱ	.4, .4	403	542	379	349	301	309	363		
	.8, .8	554	675	528	467	387	368	520		
Yield stress, kg/cm ² befh ⁱ	.4, .4	204	162	186	160	150	153	219		
	.8, .8	311	185	255	208	197	185	293		
Strain ^{cdefhⁱ}	.4, .4	.054	.033	.081	.070	.076	.069	.010		
	.8, .8	.066	.028	.077	.072	.064	.065	.011		
Mod. elas. kg/cm ² bcefh ⁱ	.4, .4	3,755	4,952	2,241	2,409	2,168	2,418	22,893		
	.8, .8	5,003	6,748	3,463	2,978	3,083	3,030	31,968		
% ash ^{bcehⁱ}	.4, .4	54.1	54.4	57.2	57.0	57.9	57.0	52.3		
	.8, .8	58.2	58.3	59.6	59.4	59.7	59.3	57.1		
Mom. inertia, cm ⁴ ehij	.4, .4	1.122	.909	.290	.174	.216	.178	.014		
	.8, .8	1.341	.931	.178	.168	.201	.210	.014		
Wall thickness, cm ^{befhⁱ}	.4, .4	.38	.48	.18	.18	.17	.17	.14		
	.8, .8	.43	.54	.19	.19	.19	.21	.15		

^aPooled across age and sex.^bCa,P level effect (P<.01).^cCa,P level X age interaction (P<.01).^dCa,P level X sex interaction.^eCa,P level X bone interaction (P<.01).^fCa,P level X age X bone interaction (P<.01).^hBone effect (P<.01).ⁱBone X age interaction (P<.01).^jBone X sex interaction (P<.01).

determine the strength of vertebrae were different from those used for other bones; thus, the results of these tests are presented separately in table 6.

When pooled across bone and sex, the data indicate that the feeding of higher levels of Ca,P resulted in an increase in the mechanical properties (bending moment, ultimate stress, yield stress and modulus of elasticity), geometrical measurements (moment of inertia and wall thickness) and percentage of ash of bones (table 3). Other researchers have also reported an increase in bone strength due to an increase in the level of Ca and P fed (Miller *et al.*, 1962, 1964; Libal *et al.*, 1969; Cromwell *et al.*, 1972; Tanksley *et al.*, 1976; Nimmo *et al.*, 1980). Interactions did occur which indicated that the response of each bone to Ca,P level was not the same across the age periods evaluated in this study.

With both levels of Ca,P, bending moment and moment of inertia of bones increased linearly across all age periods. When expressed as force per unit area, ultimate stress was lower at A3 than at A1 for pigs fed either level of Ca,P, although the decrease was not as great for pigs fed T2 as it was for pigs fed T1. The decrease in ultimate stress differed depending upon which bone was considered; this will be discussed in more detail later. At A5 and A7, bones from pigs fed T1 showed an increase in ultimate stress, while bones from pigs fed T2 had a similar ultimate stress at these ages.

For pigs fed T1, yield stress of bones in response to ultimate stress was similar across all age periods. Likewise, yield stress of bones from pigs fed T2 did not differ due to age.

Like stress, the modulus of elasticity decreased at A3 then increased at A5 and A7 for bones from pigs fed T1, while for bones from pigs fed T2, the modulus of elasticity increased linearly up to A5 and then leveled off between A5 and A7.

Percentage of ash and wall thickness increased linearly for bones from pigs fed T1 across all age periods, but among pigs fed T2, percentage of ash and wall thickness were similar at A5 and A7. Interactions did occur which indicate that not all bones responded similarly at each age period or Ca,P level.

There were no differences due to sex in the amount of force (bending moment) that the bones withstood (table 4). Bones from boars had a larger moment of inertia than bones from barrows or gilts, and when force was expressed per unit of bone area, bones from boars had a

lower ultimate and yield stress ($P < .01$) than those for barrows, while bones from gilts withstood the greatest stresses. The lower stress indicates that the boars had bones that were less mineralized than those of gilts or barrows and that the boars compensated for this lower strength by the increase in moment of inertia. This hypothesis is supported by a trend toward a lower percentage of ash in bones from boars than in bones from gilts or barrows. Liptrap *et al.* (1970) reported no difference in bending moment between bones from gilts and boars, but when stress was calculated, boars were found to have weaker bones than gilts. In contrast, Swanson (1971) indicated that human males had stronger bones than females. Martin and Atkinson (1977) attributed the stronger bones of males to an increase in moment of inertia; in females, the moment of inertia, as well as strength, declined after 30 years of age. Bones had a lower strength regardless of the level of Ca,P fed, but all sexes responded in a positive manner to increasing levels of Ca,P.

Shown in table 5 are the results of the mechanical testing of all bones (except the vertebrae) for each Ca,P level. The results have been pooled across sex and age. The Hum withstood the greatest force (bending moment) regardless of Ca,P level fed. The MC and MT bones had a




Figure 3. Stress:strain curve for bones pooled across Ca,P levels, age and sex.—region of curve where bone exhibits plastic flow.—region of curve where bone exhibits elastic flow.

TABLE 6. EFFECT OF CALCIUM-PHOSPHORUS LEVELS, AGE AND SEX ON VERTEBRA CHARACTERISTICS

Characteristic	% Ca,P															
	.4, .4				.8, .8				.4, .4				.8, .8			
Age	1	3	5	7	1	3	5	7	1	3	5	7	1	3	5	7
Max. shear stress, kg/cm ² abcd																
Gilts	165	245	400	481	164	289	520	802								
Barrows	172	252	388	480	278	400	453	668								
Boars	180	313	388	590	188	422	657	616								
Wall thickness, cm ^{abc}																
Gilts	.043	.051	.064	.073	.063	.101	.087	.110								
Barrows	.039	.045	.053	.071	.045	.095	.107	.091								
Boars	.047	.034	.057	.068	.059	.087	.132	.089								
% ash ^{abc}																
Gilts	47.3	50.2	53.1	57.1	50.6	55.1	57.4	57.8								
Barrows	45.4	50.1	53.3	55.4	49.7	56.3	58.1	58.1								
Boars	46.2	48.8	52.8	54.5	48.3	56.0	57.9	57.6								

^aCa,P level effect (P<.01).^bAge effect (P<.01).^cCa,P level X age interaction (P<.05).^dCa,P level X age X sex interaction (P<.01).

lower bending moment than the Hum and Fem, but a higher bending moment than the Rib.

Ultimate and yield stresses allow comparisons to be made between bones that differ greatly in size and shape. This can be demonstrated by a comparison of the Rib with the MC and MT bones. The Rib had a much lower bending moment than the MC and MT bones, but, when expressed as force per unit area, the yield stress of the Rib was greater than, and ultimate stress equivalent to, that of metacarpal and metatarsal bones. The modulus of elasticity of the Rib was much greater than that of all other bones because of the small amount of strain or bending that occurred in the Rib. This indicates that the Rib is a very brittle bone.

The Hum had a greater ultimate stress than the Fem. The yield stress of the Fem was greater than that of the Hum. These results indicate that the Hum withstood less force than the Fem before permanent damage (elastic flow) occurred (figure 3), but that the Hum withstood more force than the Fem after permanent damage had occurred (plastic flow). This relationship can be explained in part by the shape of the Hum. The top wall area at the point of loading in the Hum cross section (see cross section of Hum, figure 2) is much thinner than the sides and bottom. The Hum failed first at the top wall and began plastic flow (yield point) while the sides and bottom were undergoing elastic flow. The sides and bottom of the Hum withstood a greater force than the top.

From the data presented in table 5, it is evident that any relationship between percentage of ash and any of the bone strength characteristics depends upon which bone is used. For example, while the Fem and Hum have a higher ultimate stress than MC, MT or Rib bone, their percentage of ash is smaller than that of the MC or MT bone but greater than that of the Rib. Tests for homogeneity of slopes between percentage of ash and all bone strength parameters except bending moment were nonsignificant, indicating that there is little relationship between percentage of ash and strength parameters. Currey (1969) reported an exponential relationship between strength and percentage of ash. The relationship between percentage of ash and bending moment was dependent not only on bone, as mentioned above, but also upon sex ($P < .05$).

The results of the hardness test with the vertebrae sections are shown in table 6. Maximum shear stress shows a different response

from that seen in the mechanical tests with the other bones in that interactions occurred between Ca,P level, age and sex. At A1, Ver of gilts and boars did not respond to increased levels of Ca,P. At A7, Ver from gilts showed a greater response to levels of Ca,P than did those from barrows or boars. In fact, Ver from boars responded very little to level of Ca,P, and shear stress actually decreased between A5 and A7 for Ver from boars fed T2. Shear stress of Ver from barrows appeared to increase with the higher levels of Ca and P at all age periods. Percentage of ash in Ver from pigs fed T1 tended to increase across all age periods, while among pigs fed T2, percentage of ash increased at A1, A3 and A5 but did not change between A5 and A7. Thickness of the cortical bone followed a response pattern similar to that observed for percentage of ash; the response was linear for bones from pigs fed T1 and quadratic for those from pigs fed T2.

The effect of Ca,P level and age upon the ultimate stress of each bone is shown in figure 4. In this three-dimensional histogram, many of the interactions noted earlier can be observed. In the Fem of pigs fed T1, ultimate stress increased across all age periods, while the ultimate stress of the Fem of pigs fed T2 increased between A1 and A3, leveled off between A3 and A5 and then decreased at A7. The Hum of pigs fed T1 showed a response similar to that of the Fem, increasing across all age periods. The Hum of pigs fed T2 increased up to A5 and then leveled off between A5 and A7. The MC and MT bones showed no response to Ca,P levels at A1. At A3, ultimate stress values for MC and MT bones were less than those for the same bones at A1. From A3 on, the ultimate stress of the MC and MT bones




Figure 4. Effect of age and Ca,P levels on ultimate stress of various bones. ■ = pigs fed T1. ■ ■ = increase beyond T1 for pigs fed T2.

increased in a linear manner regardless of Ca,P level fed. Of all the bones, only the 4MT failed to show an increase in ultimate stress at A7 in pigs fed T2 as compared to those fed T1. The Rib of pigs fed T1 maintained a similar ultimate stress at A1 through A5 and then increased dramatically between A5 and A7. Among pigs fed T2, the Rib increased in ultimate stress across all age periods. The shear stress of Ver increased across all age periods regardless of Ca,P level fed, and, in all cases, the Ver of pigs fed T2 had a greater shear stress than the Ver of those fed T1.

Thus, in assessing mineralization in bones of pigs at different age periods, it should be noted that the Fem, Hum and Rib were the only bones to show a response to levels of Ca and P at an early age (A1); hence, they would be the bones to choose for testing in 2-month-old pigs. At A3 or A5, all bones tended to respond to levels of Ca,P, and the bones of the front or hind feet, which are usually more accessible, could be selected. At A7, only the Hum, 3MC, 4MC, 3MT and Ver responded to levels of Ca,P. The results support the conclusion of Tanksley (1979) that differences in Ca and P requirements may depend upon the bone one uses to assess requirements, but do not support his conclusion that the Fem is a better indicator of bone development than are MC bones.

Literature Cited

- Baker, J. L. and C. G. Haugh. 1979. Mechanical properties of bone: A review. *Trans. Amer. Soc. Agr. Eng.* 22:678.
- Barr, A. J., J. H. Goodnight, J. P. Sall and J. T. Helwig. 1976. *A User's Guide to SAS*. SAS Institute Inc., Raleigh, NC.
- Burnett, E. A. 1908. The effect of food on breaking strength of bones. *Agr. Exp. Sta. Bull.* 107, Vol. 21, Article 1.
- Cromwell, G. L., V. W. Hays, C. W. Scherer and J. R. Overfield. 1972. Effects of dietary calcium and phosphorus on performance and carcass, metacarpal and turbinates characteristics of swine. *J. Anim. Sci.* 34:746.
- Currey, J. D. 1969. The mechanical consequences of variation in the mineral content of bone. *J. Biomech.* 2:1.
- Evans, J. G. 1973. *Mechanical Properties of Bone*. Charles C. Thomas, Springfield, IL.
- Granik, G. and I. Stein. 1973. Human ribs: Static testing as a promising medical application. *J. Biomech.* 6:237.
- Griffel, W. 1966. *Handbook of Formulas for Stress and Strain*. Frederick Ungar Publishing Co., New York.
- Hayes, S. H., G. L. Cromwell, T. S. Stahly and T. H. Johnson. 1979. Availability of phosphorus in corn, wheat and barley for the chick. *J. Anim. Sci.* 49:992.
- Henrikson, P. A. 1968. Periodontal disease and calcium deficiency. *Acta Odontol. Scand.* 26 (Suppl. 50):1.
- Libal, G. W., E. R. Peo, Jr., R. P. Andrews and P. E. Viperman, Jr. 1969. Levels of calcium and phosphorus for growing finishing swine. *J. Anim. Sci.* 28:331.
- Liptrap, D. O., E. R. Miller, D. E. Ullrey, K. K. Keahey and J. A. Hoefler. 1970. Calcium levels for developing boars and gilts. *J. Anim. Sci.* 31:540.
- Martin, R. B. and P. J. Atkinson. 1977. Age and sex-related changes in the structure and strength of the human femoral shaft. *J. Biomech.* 10:223.
- Miller, E. R., D. E. Ullrey, C. L. Zutaut, B. V. Baltzer, D. A. Schmidt, J. A. Hoefler and R. W. Luecke. 1962. Calcium requirement of the baby pig. *J. Nutr.* 77:7.
- Miller, E. R., D. E. Ullrey, C. L. Zutaut, B. V. Baltzer, D. A. Schmidt, J. A. Hoefler and R. W. Luecke. 1964. Phosphorus requirement of the baby pig. *J. Nutr.* 82:34.
- Nimmo, R. D., E. R. Peo, Jr., B. D. Moser, P. J. Cunningham, D. G. Olson and T. D. Crenshaw. 1980. Effect of various levels of dietary calcium and phosphorus on performance, blood and bone parameters in growing boars. *J. Anim. Sci.* 51:100.
- NRC. 1973. *Nutrient Requirements of Domestic Animals, No. 2. Nutritional Requirements of Swine*. National Academy of Sciences-National Research Council, Washington, DC.
- Pond, W. G., F. E. Lovelace, E. R. Walder and L. Krook. 1969. Distribution of parenterally administered ⁴⁵Ca in bones of growing pigs. *J. Anim. Sci.* 29:298.
- Steel, R.G.D. and J. G. Torrie. 1960. *Principles and Procedures of Statistics*. McGraw-Hill Book Co., New York.
- Swanson, S.A.V. 1971. Biomechanical characteristics of bone. In R. M. Kennidi (Ed.) *Advances in Biomedical Engineering*. Academic Press, New York.
- Tanksley, T. D. 1979. Nutrition and management of the breeding herd. *Proc. Alabama Pork Ind. Conf.*, Auburn, AL.
- Tanksley, T. D., Jr., J. Schroder and R. G. Robinson. 1976. Calcium and phosphorus requirements of large framed developing boars. *Proc. Internat'l Pig Vet. Soc. Ames, IA.*
- Weir, J. D. de V., G. H. Bell and J. W. Chambers. 1949. The strength and elasticity of bone in rats on a rachitogenic diet. *J. Bone Joint Surg.* 31B:444.